


THE COPPER TUBE HANDBOOK



Copper Development Association

TABLE OF CONTENTS

INTRODUCTION	6
UNDERSTANDING COPPER TUBE	
I. STANDARD TUBES	8
Types of Copper Tube	8
Properties	8
Identification of Copper Tube	8
II. SELECTING THE RIGHT TUBE FOR THE JOB	9
Advantages of Copper Tube	9
Recommendations for Various Applications	9
III. DESIGN AND INSTALLATION DATA	10
Pressure System Sizing	10
Pressure Ratings and Burst Strength	12
Drainage Plumbing Systems	12
Copper Tube for Heating Systems	13
Ground Source Heat Pumps	14
Nonflammable Medical Gas Piping Systems	14
Snow-Melting Systems	15
Irrigation and Agricultural Sprinkler Systems	15
Solar Energy Systems	15
General Considerations	16
TECHNICAL DATA	
TABLES: TABLE 1. Copper Tube: Types, Standards, Applications, Tempers, Lengths.....	20
TABLE 2. Dimensions and Physical Characteristics of Copper Tube:	
2a: Type K.....	21
2b: Type L.....	21
2c: Type M.....	22
2d: DWV	22
2e: ACR Tube for Air Conditioning and Refrigeration Field Service.....	23
2f: Medical Gas, K and L	24

TABLE 3. Rated Internal Working Pressure for Copper Tube:	
3a. Type K.....	25
3b. Type L.....	25
3c. Type M.....	26
3d. DWV.....	26
3e. ACR.....	27
TABLE 4. Pressure-Temperature Ratings for Copper Tube Joints.....	28
TABLE 5. Actual Burst Pressures, Type K, L and M Copper Water Tube, psi at Room Temperature.....	29
TABLE 6. Pressure Loss Due to Friction in Type M Copper Tube.....	30
TABLE 7. Pressure Loss in Fittings and Valves Expressed as Equivalent Lengths of Tube.....	32
TABLE 8. Radii of Coiled Expansion Loops and Developed Lengths of Expansion Offsets.....	35
TABLE 9. Dimensions of Solder Joint Ends for Wrought and Cast Fittings.....	37
TABLE 10. Solder Requirements for Solder-Joint Pressure Fittings.....	39
TABLE 11. Typical Brazing Filler Metal Consumption.....	40
TABLE 12. Filler Metals for Brazing.....	40
FIGURES: FIGURE 1. Arrangement for Anchoring DWV Stack Passing through a Concrete Floor.....	13
FIGURE 2. Collapsing Pressures of Copper Tube, Types K, L and M.....	33
FIGURE 3. Expansion vs. Temperature Change for Copper Tube.....	34
FIGURE 4 a,b,c. Coiled Expansion Loops and Expansion Offsets.....	35
FIGURE 5. Selected Pressure Fittings.....	36
FIGURE 6. Dimensions of Solder Joint Fitting Ends.....	37
FIGURE 7. Melting Temperature Ranges for Copper and Copper Alloys, Brazing Filler Metals, Flux and Solders.....	38
FIGURE 8. Brazing Flux Recommendations.....	39

WORKING WITH COPPER TUBE

IV. BENDING	42
TABLE: TABLE 13. Bending Guide for Copper Tube.....	42
FIGURE: FIGURE 9. Bending Using a Lever-Type Hand Bender.....	42
V. JOINING	43
Fittings.....	43
Solders.....	43
Fluxes.....	44

TABLE OF CONTENTS\continued

VI.	SOLDERED JOINTS	45
	Measuring and Cutting	45
	Reaming	45
	Cleaning	46
	Applying Flux	46
	Assembly and Support	47
	Heating	47
	Applying Solder	48
	Cooling and Cleaning	48
	Testing	48
FIGURES:	FIGURE 10. Measuring	45
	FIGURE 11. Cutting	45
	FIGURE 12. Reaming: File	45
	FIGURE 13. Reaming: Pocket Knife	46
	FIGURE 14. Reaming: Deburring Tool	46
	FIGURE 15. Cleaning: Sand Cloth	46
	FIGURE 16. Cleaning: Abrasive Pad	46
	FIGURE 17. Cleaning: Fitting Brush	46
	FIGURE 18. Fluxing: Tube	46
	FIGURE 19. Fluxing: Fitting	47
	FIGURE 20. Assembly	47
	FIGURE 21. Removing Excess Flux	47
	FIGURE 22. Pre-Heating Tube	47
	FIGURE 23. Pre-Heating Fitting	47
	FIGURE 24. Electric Resistance Hand Tool	48
	FIGURE 25. Soldering	48
	FIGURE 26. Cleaning	48
	FIGURE 27. Schematic of Solder Joint	48

VII.	BRAZED JOINTS	49
	Brazing Filler Metals	49
	Fluxes	49
	Assembling	49
	Applying Heat and Brazing	50
	Horizontal and Vertical Joints	50
	Removing Residue	50
	General Hints and Suggestions.....	50
	Testing	50
VIII.	FLARED JOINTS	51
FIGURES:	FIGURE 28. Flare Fitting/Flared Joint During Assembly	51
	FIGURE 29. Completed Flared Joint	51
	FIGURE 30. Reaming Prior to Flaring the Tube End	51
	FIGURE 31. Lowering the Flaring Cone into the Tube End	52
	FIGURE 32. Completed Flared Tube End	52
IX.	ADDITIONAL JOINING METHODS	53
FIGURES:	FIGURE 33. Tee-Pulling Tool	53
	FIGURE 34. Mechanical Coupling System.....	53

APPENDIX

X.	ORGANIZATIONS AND THEIR ABBREVIATIONS	54
-----------	--	----

NOTICE: This Handbook has been prepared for the use of journeymen plumbers, pipefitters, refrigeration fitters, sprinkler fitters, plumbing and heating contractors, engineers, and others involved in the design or installation of plumbing, heating, air-conditioning, refrigeration and other related systems. It has been compiled from information sources Copper Development Association Inc. (CDA) believes to be competent. However, recognizing that each system must be designed and installed to meet the particular circumstances, CDA assumes no responsibility or liability of any kind in connection with this Handbook or its use by any person or organization and makes no representations or warranties of any kind hereby.

INTRODUCTION

Since primitive man first discovered copper, the red metal has constantly served the advancement of civilization. Archaeologists probing ancient ruins have discovered that this enduring metal was a great boon to many peoples. Tools for handicraft and agriculture, weapons for hunting, and articles for decorative and household uses were wrought from copper by early civilizations. The craftsmen who built the great pyramid for the Egyptian Pharaoh Cheops fashioned copper pipe to convey water to the royal bath. A remnant of this pipe was unearthed some years ago still in usable condition, a testimonial to copper's durability and resistance to corrosion.

Modern technology, recognizing that no material is superior to copper for conveying water, has reconfirmed it as the prime material for such purposes. Years of trouble-free service in installations here and abroad have built a new reputation for copper piping in its modern form—light, strong, corrosion resistant tube. It serves all kinds of buildings: single-family homes, high-rise apartments and industrial, commercial and office buildings.


Today, copper tube for the plumbing, heating and air-conditioning industries is available in drawn and annealed tempers (referred to in the trades as "hard" and "soft") and in a wide range of diameters and wall

thicknesses. Readily available fittings serve every design application. Joints are simple, reliable and economical to make—additional reasons for selecting copper tube.

Today, nearly 5,000 years after Cheops, copper developments continue as the industry pioneers broader uses for copper tube in engineered plumbing systems for new and retrofitted residential, industrial and commercial installations.



UNDERSTANDING COPPER TUBE



I. STANDARD TUBES

Long lasting copper tube is a favorite choice for plumbing, heating, cooling and other systems. In the United States, it is manufactured to meet the requirements of specifications established by the American Society for Testing and Materials (ASTM).

All tube supplied to these ASTM standards is a minimum of 99.9 percent pure copper. The copper customarily used for tube supplied to these specifications is deoxidized with phosphorus and referred to as C12200 (Copper No. 122) or DHP¹ Copper. Other coppers may also be used.

Types of Copper Tube

Table 1, page 20, identifies the six standard types of copper tube and their most common applications.² The table also shows the ASTM Standard appropriate to the use of each type along with a listing of its commercially available lengths, sizes and tempers.

Types K, L, M, DWV and Medical Gas tube are designated by ASTM standard sizes, with the actual outside diameter always $\frac{1}{8}$ -inch larger than the standard size designation. Each type represents a series of sizes with different wall thicknesses. Type K tube

has thicker walls than Type L tube, and Type L walls are thicker than Type M, for any given diameter. All inside diameters depend on tube size and wall thickness.

Copper tube for air-conditioning and refrigeration field service (ACR) is designated by actual outside diameter.

“Temper” describes the strength and hardness of the tube. In the piping trades, drawn temper tube is often referred to as “hard” tube and annealed as “soft” tube. Tube in the hard temper condition is usually joined by soldering or brazing, using capillary fittings or by welding.

Tube in the soft temper can be joined by the same techniques and is also commonly joined by the use of flare-type and compression fittings. It is also possible to expand the end of one tube so that it can be joined to another by soldering or brazing without a capillary fitting—a procedure that can be efficient and economical in many installations.

Tube in both the hard and soft tempers can also be joined by a variety of “mechanical” joints that can be assembled without the use of the heat source required for soldering and brazing.

Properties

The dimensions and other physical characteristics of Types K, L, M and DWV tube are given in **Tables 2a, b, c and d**, pages 21-22. All four types are used for both pressure and non-pressure applications within the range of their respective safe working pressures as described in **Tables 3a, b, c and d** on pages 25-26.

The dimensions and physical characteristics of ACR tube and Medical Gas tube are given in **Tables 2e and f**, pages 23-24.

Identification of Copper Tube

Copper tube, Types K, L, M, DWV and Medical Gas, must be permanently marked (incised) in accordance with its governing specifications to show tube type, the name or trademark of the manufacturer, and the country of origin. In addition to incised markings, hard tube will have this information printed on it in a color which distinguishes its tube type (See **Table 1**). Soft ACR tube may not carry any incised or color markings. Hard ACR tube is color marked only.

¹ Phosphorous-Deoxidized, High Residual Phosphorous Copper

² There are many other copper and copper alloy tubes and pipes available for specialized applications. For more information on these products contact the Copper Development Association Inc.

II. SELECTING THE RIGHT TUBE FOR THE JOB

Advantages of Copper Tube

Strong, corrosion resistant, copper tube is the leading choice of modern contractors for plumbing, heating and cooling installations in all kinds of residential and commercial buildings. There are seven primary reasons for this:

1. **Copper is economical.** The combination of easy handling, forming and joining permits savings in installation time, material and overall costs. Long-term performance and reliability mean fewer callbacks, and that makes copper the ideal cost-effective tubing material.

2. **Copper is lightweight.** Copper tube does not require the heavy thickness of ferrous or threaded pipe of the same internal diameter. This means copper costs less to transport, handles more easily and, when installed, takes less space.

3. **Copper is formable.** Because copper tube can be bent and formed, it is frequently possible to eliminate elbows and joints. Smooth bends permit the tube to follow contours and corners of almost any angle. With soft temper tube, particularly when used for renovation or modernization projects, much less wall and ceiling space is needed.

4. **Copper is easy to join.** Copper tube can be joined with capillary fittings. These fittings save material and make smooth, neat, strong and leak-proof joints. No extra thickness or weight is necessary to compensate for material removed by threading.

5. **Copper is safe.** Copper tube will not burn or support combustion and decompose to toxic gases. Therefore, it will not carry fire through floors, walls and ceilings. Volatile organic compounds are not required for installation.

6. **Copper is dependable.** Copper tube is manufactured to well-defined

composition standards and marked with permanent identification so you know exactly what it is and who made it. It is accepted by virtually every plumbing code.

7. Copper resists corrosion.

Excellent resistance to corrosion and scaling assures long, trouble-free service, which means satisfied customers.

Minimum Recommendations for Various Applications

It is up to the designer to select the type of copper tube for use in a particular application. Strength, formability and other mechanical factors often determine the choice. Plumbing and mechanical codes govern what types may be used. When a choice can be made, it is helpful to know which type of copper tube has and can serve successfully and economically in the following applications:

Underground Water Services—

Use Type M hard for straight lengths joined with fittings, and Type L soft where coils are more convenient.

Water Distribution Systems—

Use Type M for above and below ground.

Chilled Water Mains—

Use Type M for all sizes.

Drainage and Vent Systems—

Use Type DWV for above- and below-ground waste, soil and vent lines, roof and building drains and sewers.

Heating—For radiant panel and hydronic heating and for snow melting systems, use Type L soft temper where coils are formed in place or prefabricated, Type M where straight lengths are used. For water heating and low-pressure steam, use Type M for all sizes. For condensate return lines, Type L is successfully used.

Solar Heating—See Heating section above. For information on solar installation and on solar collectors, write CDA. (See also page 15.)

Fuel Oil, L.P. and Natural Gas Services—Use Type L or Type ACR tube with flared joints in accessible locations and brazed joints made using AWS A5.8 BAg series brazing filler metals in concealed locations.

Nonflammable Medical Gas Systems—Use Medical Gas tube Types K or L, suitably cleaned for oxygen service per NFPA Standard No. 99, *Health Care Facilities*.

Air-Conditioning and Refrigeration Systems—Copper is the preferred material for use with most refrigerants. Use Types L, ACR or as specified.

Ground Source Heat Pump Systems—Use Types L or ACR where the ground coils are formed in place or prefabricated, or as specified.

Fire Sprinkler Systems—Use Type M hard. Where bending is required, Types K or L are recommended. Types K, L and M are all accepted by NFPA.

Low Temperature Applications—Use copper tube of Type determined by rated internal working pressures at room temperature as shown in Table 3. Copper tube retains excellent ductility at low temperatures to -452°F and yield strength and tensile strength increase as temperature is reduced to this point. This plus its excellent thermal conductivity makes an unusual combination of properties for heat exchangers, piping, and other components in cryogenic plants and other low temperature applications.

Compressed Air—Use copper tube of Types K, L or M determined by the rated internal working pressures as shown in Table 3. Brazed joints are recommended.

III. DESIGN AND INSTALLATION DATA

Pressure System Sizing

Designing a copper tube water supply system is a matter of determining the minimum tube size for each part of the total system by balancing the interrelationships of six primary design considerations:

1. Available main pressure;
2. Pressure required at individual fixtures;
3. Static pressure losses due to height;
4. Water demand (gallons per minute) in the total system and in each of its parts;
5. Pressure losses due to the friction of water flow in the system;
6. Velocity limitations based on noise and erosion.

Design and sizing must always conform to applicable codes. But in the final analysis, design must also reflect judgment and results of engineering calculations. Many codes, especially the model codes, include design data and guidelines for sizing water distribution systems and also include examples showing how the data and guidelines are applied.

Small Systems—Distribution systems for single-family houses usually can be sized easily on the basis of experience and applicable code requirements, as can other similar small installations. Detailed study of the six design considerations above is not necessary in such cases.

In general, the mains that serve fixture branches can be sized as follows:

- Up to three $\frac{3}{8}$ -inch branches can be served by a $\frac{1}{2}$ -inch main.
- Up to three $\frac{1}{2}$ -inch branches

can be served by a $\frac{3}{4}$ -inch main.

- Up to three $\frac{3}{4}$ -inch branches can be served by a 1-inch main.

The sizing of more complex distribution systems requires detailed analysis of each of the sizing design considerations listed above.

Pressure Considerations—At each fixture in the distribution system, a minimum pressure of 8 psi should be available for it to function properly—except that some fixtures require a higher minimum pressure for proper function, for example:

- Flush valve for blow-out and syphon-jet closets25 psi
- Flush valves for water closets and urinals.....15 psi
- Sill cocks, hose bibbs and wall hydrants.....10 psi.

Local codes and practices may be somewhat different from the above and should always be consulted for minimum pressure requirements.

The maximum water pressure available to supply each fixture depends on the water service pressure at the point where the building distribution system (or a segment or zone of it) begins. This pressure depends either on local main pressure, limits set by local codes, pressure desired by the system designer, or on a combination of these. In any case, it should not be higher than about 80 psi (pounds per square inch).

However, the entire water service pressure is not available at each fixture due to pressure losses inherent to the system. The pressure losses include losses in flow through the water meter, static losses in lifting water to higher

elevations in the system, and friction losses encountered in flow through piping, fittings, valves and equipment.

Some of the service pressure is lost immediately in flow through the water meter, if there is one. The amount of loss depends on the relationship between flow rate and tube size. Design curves and table showing these relationships appear in most model codes and are available from meter manufacturers.

Some of the main pressure will also be lost in lifting the water to the highest fixture in the system. The height difference is measured starting at the meter, or at whatever other point represents the start of the system (or the segment or zone) being considered. To account for this, multiply the elevation of the highest fixture, in feet, by the factor 0.434, the pressure exerted by a 1-foot column of water. This will give the pressure in psi needed to raise the water to that level. For example, a difference in height of 30 feet reduces the available pressure by 13 psi ($30 \times 0.434 = 13.02$).

Friction losses in the system, like losses through the water meter, are mainly dependent on the flow rate of the water through the system and the size of the piping. To determine these losses, water demand (and thus, flow rate) of the system must first be determined.

Water demand—Each fixture in the system represents a certain demand for water. Some examples of approximate water demand in gallons per minute (gpm) of flow, are:

Drinking fountain..... 0.75

Lavatory faucet.....	2.0
Lavatory faucet, self closing.....	2.5
Sink faucet, WC tank ball cock.....	3.0
Bathtub faucet, shower head, laundry tub faucet.....	4.0
Sill cock, hose bibb, wall hydrant.....	5.0
Flush valve (depending on design.....)	3.5
Shower head	2.2

Adding up numbers like these to cover all the fixtures in an entire building distribution system would give the total demand for water usage in gpm, if all of the fixtures were operating and flowing at the same time—which of course does not happen. A reasonable estimate of demand is one based on the extent to which various fixtures in the building might actually be used simultaneously. Researchers at the National Institute of Standards and Technology studied this question some years ago. They applied probability theory and field observations to the real-life problem of simultaneous usage of plumbing fixtures.

The result was a system for estimating total water demand which is based on reasonable assumptions about the likelihood of simultaneous usage of fixtures. Out of this study came the concept of *fixture units*.

Each type of fixture is assigned a fixture unit value which reflects (1) its demand for water, that is, the flow rate into the fixture when it is used, (2) the average time duration of flow when the fixture is used, and (3) the frequency with which the fixture is likely to be used. Assigned fixture unit values vary by jurisdiction. Consult local plumbing codes for values used in your area.

Totaling the fixture unit values for all the fixtures in a system, or for any part of the distribution system, gives a measure of the load combined fixtures impose on the plumbing distribution and supply system. This fixture unit total may be translated into expected maximum water demand following the procedure prescribed by your local code.

Keep in mind the demand calculations just described apply to fixtures that are used *intermittently*. To this must be added the actual demand in gpm for any fixtures which are designed to run continuously when they are in use; for example, air-conditioning systems, lawn sprinkler systems and hose bibbs.

Pressure Losses Due to Friction—The pressure available to move the water through the distribution system (or a part of it) is the main pressure minus: (1) the pressure loss in the meter, (2) the pressure needed to lift water to the highest fixture (static pressure loss), and (3) the pressure needed at the fixtures themselves. The remaining available pressure must be adequate to overcome the pressure losses due to friction encountered by the flow of the total demand (intermittent plus continuous fixtures) through the distribution system and its various parts. The final operation then is to select tube sizes in accordance with the pressure losses due to friction.

In actual practice, the design operation may involve repeating the steps in the design process to readjust pressure, velocity and size to achieve the best balance of main pressure, tube size, velocity and available pressure at the fixtures for the design flow required in the various parts of the system.

Table 6, page 30, shows the relationship among flow, pressure drop due to friction, velocity and tube size for Types K, L and M copper water tube. These are the data required to complete the sizing calculation. **NOTE: Values are not given for flow rates that exceed the maximum recommendation for copper tube.**

For the tube sizes above about 1¹/₄ inch, there is virtually no difference among the three types of tube in terms of pressure loss. This is because the differences in cross sectional area of these types become insignificant as tube size increases. In fact, for this reason, the value for Type M tube given in **Table 6** can be used for DWV tube as well.

Pressure loss values in **Table 6** are given per linear foot of tube. In measuring the length of a system or of any of its parts, the total length of tube must be measured, and for close estimates, an additional amount must be added on as an allowance for the extra friction losses that occur as a result of valves and fittings in the line. **Table 7**, page 32, shows these allowances for various sizes and types of valves and fittings.

Water Velocity Limitations — To avoid excessive system noise and the possibility of erosion-corrosion, the designer should not exceed flow velocities of 8 feet per second for cold water and 5 feet per second in hot water up to approximately 140°F. In systems where water temperatures routinely exceed 140°F, lower flow velocities such as 2 to 3 feet per second should not be exceeded. In addition, where 1/2-inch and smaller tube sizes are used, to guard against localized high velocity turbulence due to possibly faulty workmanship (e.g. burrs at tube ends which were not properly reamed/deburred) or unusually numerous, abrupt changes in flow direction, lower velocities should be considered. Locally aggressive water conditions can combine with these two considerations to cause erosion-corrosion if system velocities are too high.

Due to constant circulation and elevated water temperatures, particular attention should be paid to water velocities in circulating hot water systems. Both the supply and return piping should be sized such that the maximum velocity does not exceed the above recommendations. Care should be taken to ensure that the circulating pump is not oversized, and that the return piping is not undersized, both common occurrences in installed piping systems.

Table 6 applies to copper tube only, and should not be used for other plumbing materials. Other materials require additional allowances for corrosion, scaling and caking *which are not necessary for copper*. This is because copper normally maintains its smooth bore throughout its service life.

Pressure Ratings and Burst Strength

As for all materials, the allowable internal pressure for any copper tube in service is based on the formula used in the American Society of Mechanical Engineers Code for Pressure Piping (ASME B31):

$$P = \frac{2S(t_{\min} - C)}{D_{\max} - 0.8(t_{\min} - C)}$$

where:

P = allowable pressure, psi

S = maximum allowable stress in tension, psi

t_{\min} = wall thickness (min.), in.

D_{\max} = outside diameter (max.), in.

C = a constant

For copper tube, because of copper's superior corrosion resistance, the B31 code permits the factor C to be zero. Thus the formula becomes:

$$P = \frac{2St_{\min}}{D_{\max} - 0.8t_{\min}}$$

The value of S in the formula is the maximum allowable stress (ASME B31) for continuous long-term service of the tube material. It is only a small fraction of copper's ultimate tensile strength or of the burst strength of copper tube and has been confirmed to be safe by years of service experience and testing. The allowable stress value depends on the service temperature and on the temper of the tube, drawn or annealed.

In **Tables 3a, b, c and d**, pages 25-26, the rated internal working pressures are shown for both annealed (soft) and drawn (hard) Types K, L, M and DWV copper tube for service temperatures from 100°F to 400°F. The ratings for drawn tube can be used for soldered systems and systems using properly designed mechanical joints. Fittings manufacturers can provide information about the strength of their various types and sizes of fittings.

When welding or brazing is used to join tubes, the annealed ratings must be used, since the heating involved in these joining processes will anneal (soften) the hard tube. This is the reason that annealed ratings are shown in **Tables 3c** for Type M and **3d** for DWV

tube, although they are not furnished in the annealed temper. **Table 3e**, page 27, lists allowable internal working pressures for ACR tube.

In designing a system, joint ratings must also be considered, because the lower of the two ratings (tube or joint) will govern the installation. Most tubing systems are joined by soldering or brazing. Rated internal working pressures for such joints are shown in **Table 4**, page 28. These ratings are for all types of tube with standard solder joint pressure fittings and DWV fittings. In soldered tubing systems, the rated strength of the joint often governs design.

When brazing, use the ratings for annealed tube found in **Tables 3a-3e** as brazing softens (anneals) the tube near the joints (the heat affected zone). Joint ratings at saturated steam temperatures are shown in **Table 4**.

The pressures at which copper tube will actually burst are many times the rated working pressures. Compare the actual values in **Table 5**, page 29, with the rated working pressures found in **Tables 3a-3c**, pages 25-26. The very conservative working pressure ratings give added assurance that pressurized systems will operate successfully for long periods of time. The much higher burst pressures measured in tests indicate that tubes are well able to withstand unpredictable pressure surges that may occur during the long service life of the system. Similar conservative principles were applied in arriving at the working pressures for brazed and soldered joints. The allowable stresses for the soldered joints assure joint integrity under full rated load for extended periods of time. Short-term strength and burst pressures for soldered joints are many times higher. In addition, safety margins were factored into calculating the joint strengths.

Drainage Plumbing Systems

The design and installation of drainage systems range from simple to complex, depending on the type of building, the local code and the occupancy requirements. The local plumbing code will include

requirements for acceptable materials, installation and inspection, and these must be followed as the first requirement of an acceptable job.

There are usually differences—sometimes minor, sometimes quite important—among plumbing codes. Among the features which differ from code to code may be minimum tube sizes, permissible connected fixture loads, fittings and connections, methods of venting, supports and testing. Few codes are completely specific about installation details and leave the responsibility of proper and suitable installation to the designer and the contractor.

In large and multistory buildings, the design will generally require the services of a mechanical engineer and a plumbing designer. The plumbing designer has the responsibility for coordinating the drainage system design within the overall building construction requirements. A good drainage design must accommodate the problems of installation space, building movement, support, expansion and contraction, pipe sleeves, offsets and provisions for necessary maintenance.

In residential buildings and small one- and two-story commercial buildings, the drainage piping is usually straightforward in design and simple in installation. Type DWV copper tube, installed with good workmanship by an experienced plumber, will provide many years of trouble-free service.

The smaller diameter of DWV tube and fittings makes it possible to install copper drainage systems where other competing piping materials would be impossible, difficult or more costly. For example, a 3-inch copper stack has only a 3³/₈-inch outside diameter at the fitting and can be installed in a 3¹/₂-inch cavity wall.

Prefabrication—Considerable savings can be effected by prefabricating copper DWV subassemblies. Prefabrication permits work even when adverse weather prohibits activity on the job site. Simple, inexpensive jigs can be made to position the tube and fittings during assembly and help eliminate costly dimensional errors. Freedom of movement

at the bench permits joints to be made more readily than at the point of installation, where working space may be limited.

Soldered joints are strong and rigid. Subassemblies can be handled without fear of damage. The lightweight features of copper DWV tube and fittings make it possible to handle fairly large assemblies. Other dependable drainage plumbing materials may weigh three to four times as much. Subassemblies require a minimum of support when connected to a previously installed section of a drainage system.

Copper DWV tube has been used successfully for years in all parts of drainage plumbing systems for high-rise buildings—for soil and vent stacks and for soil, waste and vent branches. Copper tube's light weight and the ease with which it can be prefabricated have been especially important in high-rise drainage systems.

Expansion of DWV Systems—In high-rise buildings, expansion and contraction of the stack should be considered in the design. Possible movement of a copper tube stack as the temperature of the stack changes is about 0.001 inch per degree F per 10-foot floor. (See **Figure 3**, page 34.) This is slightly more than for iron and steel pipe and considerably less than for plastic.

Since length, temperature changes and piping design itself are all involved in expansion, the designer must determine the best way to take care of expansion in any particular installation. One simple procedure for controlling thermal movement is to anchor the stack. Anchoring at every eighth floor will take care of an anticipated maximum temperature rise of 50°F; anchoring every four floors will take care of a 100°F maximum temperature rise. Care should be taken to avoid excessive stresses in the stack anchors or structure caused by thermal growth of the stack.

Perhaps the simplest effective anchor, when the stack passes through concrete floors, is to use pipe clamps and soldered fittings as shown in **Figure 1**. The pipe clamps can be placed above and below the floor, backed up by

sliding the fittings tight against the clamps and soldering them in place. At all floors between anchors, sleeves in the concrete floors should be used to prevent lateral movement of the tube.




FIGURE 1: Arrangement for Anchoring DWV Stack Passing Through a Concrete Floor.

Hydrostatic Testing of DWV Systems—While a copper drainage system is not ordinarily operated under pressure conditions, it must withstand the pressure of a hydrostatic test. The allowable pressures for copper DWV tube and soldered joints are given in **Table 3d**, page 26, and in **Table 4**, page 28, respectively.

To determine the vertical height that can be statically pressure tested (with water) in one segment, take the lowest applicable figure from **Table 3d** and **Table 4** and multiply by 2.3. (A 2.3-foot column of water creates a pressure of 1 psi.) For example, if 50-50 tin-lead solder is used and the largest tube size is 4-inch at a service temperature of 100°F, multiply 80 (the lower of the solder joint rating of 80 in **Table 4** and the tube rating of 257 in **Table 3d**) by 2.3; the result is 184. Thus, a 184-foot vertical segment of stack could be tested at once.

If 95-5 tin-antimony solder is the joining material, the lower of the corresponding rating for 4-inch tube from the tables, 257 (the tube governs) is multiplied by 2.3, equaling 591. Thus, theoretically, 591 feet (59 ten-foot stories) could be tested at once. If the joint is brazed, the value from **Table 3d** for annealed tube (150) governs. This value multiplied by 2.3 equals 345 feet, or only 34 stories at once. The actual vertical segment height tested is usually much less and depends on practical considerations on the job.

Copper Tube for Heating Systems

Copper tube is popular for heating systems in both new and remodeled buildings. Contractors have learned through experience that, all factors considered, copper tube remains superior to any substitute material. The advantages of light weight, choice of tempers, long-term reliability, and ease of joining, bending and handling are of major importance.

For example, where rigidity and appearance are factors, drawn tube is recommended. Annealed tube is particularly suitable for panel heating, snow melting, and short runs to radiators, convectors and the like. With annealed tube the need for fittings is reduced to a minimum, saving substantial installation labor and material.

Forced circulation hot water heating systems provide uniform heating and quick response to changes in heating load, require little maintenance and can be easily zoned to provide different temperature levels throughout the buildings. These systems use the smallest and most economical tube sizes with soldered joints and require little space for the installation. Also, in combination with the heating system and where permitted by code, domestic hot water can be heated directly—eliminating the need for a separate water heater.

Design and installation data for heating systems are given in *The Heating and Air-Conditioning Guide*, published by the American Society for Heating, Refrigeration and Air-Conditioning Engineers (ASHRAE), as well as in literature published by manufacturers of boilers and other heating devices. Those publications should be consulted for detailed design.

Steam-Heating Return Lines—For steam-heating systems, especially return lines, the outstanding corrosion resistance and non-rusting characteristics of copper tube assure trouble-free service and maintenance of traps, valves and other devices. On condensate and hot water return lines, it is recommended that the last *two feet before* the heating medium should be *double* the size of the rest of the line.

For example, if the return line is 1-inch tube, enlarge it to 2-inch.

Radiant Panel Heating—A modern application of an ancient principle, radiant panel heating, can be used successfully in nearly all types of structures. In panel systems, low-temperature hot water, circulating through coils or grids of copper tube embedded in a concrete floor or plaster ceiling, warms the surfaces and the air. Panel systems offer uniform heating and comfort, an invisible heat source, complete use of the floor area, cleanliness and the elimination of dust-carrying drafts.

Copper tube is the ideal piping material for floor and ceiling panels because of its excellent heat transfer characteristics, light weight, long lengths, corrosion resistance and ease of bending, joining and handling. Soft temper tube in coils is commonly used for sinuous (curved pattern) heating layouts, since it is easily bent and joints are reduced to a minimum. Hard temper tube is used for mains, risers, heaters and grid-type heating coils.

Location of the heating panel is relatively unimportant for the comfort of room occupants, but it does depend on the architectural and thermal characteristics of the room. Floor installations have the advantage of low initial cost and are particularly suitable for garages, schools and churches. They are generally designed to operate at a maximum surface temperature of 85°F. Above this temperature, occupants become uncomfortable.

Ceiling panels can be operated at higher surface temperatures and heat output levels than floor panels. Heating panels respond quickly to changes in heating load, have low thermal storage and require only a simple control system.

The tube sizes of heating coils chiefly affect the hydraulics of the heating system and are relatively unimportant from the standpoint of heat output of the panel. For sinuous floor coils $\frac{3}{8}$ -inch, $\frac{1}{2}$ -inch and $\frac{3}{4}$ -inch soft temper tube are generally used with a 9-inch or 12-inch center-to-center

spacing. For ceiling panel installations the sinuous coils are formed of $\frac{3}{8}$ -inch soft temper tube with a tube spacing of 4 inches or 6 inches. Soldered joints are commonly used.

Ground Source Heat Pumps

Air-source heat pumps have been used for residential and commercial heating and cooling for many years. Such units rely on air-to-air heat exchange through evaporator units similar to those used for air conditioners.

More recent heat pump technology relies on circulating a refrigerant through buried copper tubing for heat exchange. These units rely on the constancy of the ground temperature below the frost level (about 55°F) for heat transfer and are considerably more efficient than their air-source counterparts. They are known variously by such terms as ground source, earth-coupled, direct exchange or geothermal.

The most efficient ground source heat pumps use ACR, Type L or special-size copper tubing buried in the ground to transfer heat to or from the conditioned space. The flexible copper tube (typically $\frac{1}{4}$ -inch to $\frac{5}{8}$ -inch) can be buried in deep vertical holes, horizontally in a relatively shallow grid pattern, in a vertical fence-like arrangement in medium-depth trenches, or as custom configurations suited to the installation.

The number of manufacturers which can supply commercial and residential ground source units is constantly growing. Contact the Copper Development Association Inc. to obtain the current listing.

Nonflammable Medical Gas Piping Systems

Safety standards for oxygen and other positive-pressure medical gases require the use of Type K or L copper tube (see ASTM B 819). Special cleanliness requirements are called for because oxygen under pressure may cause the spontaneous combustion of

some organic oils (the residual of lubricating oil used during manufacture) and for the safety of patients receiving medical gases.

Copper tube for medical gas lines is furnished by the manufacturers suitably cleaned and capped or plugged. Care must be taken to prevent contamination of the system when the caps or plugs are removed and tube is installed. The installer must satisfy himself and the inspection department that the cleanliness requirements of the code have been met.

The following requirements are based on those found in NFPA Standard No. 99, *Health Care Facilities*, Chapter 4, Gas and Vacuum Systems.

Installation and Testing of Medical Gas Piping Systems—

1. All piping, valves, fittings and other components for use in all non-flammable medical gas systems must be thoroughly cleaned by the manufacturer to remove oil, grease and other readily oxidizable materials as if they were being prepared for oxygen service. Use particular care in storage and handling. Such material must be capped or plugged to prevent recontamination before final assembly. Just prior to final assembly, the material must be examined internally for contamination.

■ Cleaning must be done in accordance with the provisions of CGA Pamphlet G-4.1, *Cleaning Equipment for Oxygen Service*.

2. All brazed joints in the piping shall be made up using brazing filler metals that bond with the base metals being brazed and that comply with *Specification for Brazing Filler Metal*, ANSI/AWS A5.8.

■ Copper-to-copper joints shall be made using a copper-phosphorus brazing filler metal (BCuP series) without flux.

■ Dissimilar metals such as copper and brass shall be joined using an appropriate flux with either a copper-phosphorus (BCuP series) or a silver (BAg series) brazing filler metal. Apply flux sparingly to the clean tube only and in a manner to avoid leaving any excess inside of completed joints.

(NOTE: Ensure proper ventilation. Some BA series filler metals contain cadmium, which, when heated during brazing, can produce toxic fumes.)

■ During brazing, the system shall be continuously purged with oil-free dry nitrogen to prevent the formation of scale within the tubing. The purge shall be maintained until the joint is cool to the touch.

■ The outside of all tubes, joints and fittings shall be cleaned by washing with hot water after assembly to remove any excess flux and provide for clear visual inspection of brazed connections.

■ A visual inspection of each brazed joint shall be made to assure that the alloy has flowed completely around the joint at the tube-fitting interface. Where flux has been used, assure that solidified flux residue has not formed a temporary seal that could hold test pressure.

3. Threaded joints in piping systems shall be tinned or made up with polytetrafluoroethylene (such as Teflon®) tape or other thread sealants suitable for oxygen services. Sealants shall be applied to the male threads only.

Snow-Melting Systems

Snow-melting systems, installed in walks, driveways, loading platforms and other paved areas, are an efficient, economical means of snow, sleet and ice removal. To warm the surface, a 50-50 solution of water and antifreeze is circulated through copper tube embedded in the concrete or blacktop. Considerable savings can be realized at industrial plant installations where waste heat sources can be utilized.

In general, installation of snow melting coils is similar to that of floor panel heating coils. Selection of a sinuous or a grid pattern for a snow-melting system depends largely on the shape, size and installation conditions. Grids are good for square and rectangular areas; sinuous coils are usually preferred for irregular areas. The lower pressure loss with a grid configuration permits the use of smaller diameter tube saving material costs. Maximum economy is often realized

with a combination of sinuous and grid-type coils.

Soft temper copper tube is suitable for both sinuous and grid-type coils; hard temper is better for larger grid coils and for mains. Soft tube facilitates the installation of sinuous coils because of its long lengths and ease of bending which reduce the number of joints to a minimum.

The solution temperature entering the snow melting coils should be 120°F to 130°F. To obtain a heating effect for snow melting of 100 BTU per hour per square foot with copper tube spaced on 12-inch centers in concrete (or 9-inch centers in blacktop), a maximum of 140 feet of 1/2-inch tube or 280 feet of 3/4-inch tube may be used. To obtain a heat input of 200 BTU per hour per square foot of snow area, a maximum of 60 feet of 1/2-inch tube or 150 feet of 3/4-inch tube may be used.

Tube in concrete should be located about 1/4 to 1/2 inches below the surface. The concrete should be reinforced with wire mesh. In blacktop, 1/2 inches minimum of compacted thickness of blacktop should cover the tube. The tube should be laid with care on compacted gravel, crushed stone or a concrete base. Allowances should be made for lateral movement where the tube enters and leaves the concrete or blacktop.

The same types of heaters and circulating pumps available for radiant heating installations are suitable for snow-melting panels. The panels also may be hooked up to a building's space heating system, if the system has sufficient capacity for the additional load and satisfactory precautions against freezing can be made.

Irrigation and Agricultural Sprinkler Systems

Irrigation systems are necessities in arid agricultural areas, and sprinkling systems for maintaining landscaped areas are being used increasingly. Regardless of type or size of system, many successful installations testify that copper is the ideal tube material for the lines.

With the aid of pressure loss and velocity relationships shown in **Table 6**, page 30, and the instruction contained in the literature of pump and sprinkler manufacturers, plumbers can lay out a copper tube watering system to service lawns, crops or golf courses.

System lines should be laid deep enough to avoid mechanical damage by tools and they should be pitched to drain freely. Where freezing can be expected, the system should be installed below the frost line.

Expansion and contraction should not be a problem as long as lines are not rigidly anchored.

Solar Energy Systems

The energy crises in the 1970s provided an economic impetus and a national commitment to use solar energy for heating. Solar energy systems to heat domestic water and for space heating are based on adding a collector to the heating system to capture energy from the sun. In general, this simply involves extending the heating/plumbing system to the roof of the house, where a solar collector is incorporated into it.

CDA published a design handbook for solar energy systems which includes an easy-to-use method for properly sizing a solar heating system to achieve desired solar contributions. For a copy of the handbook, please write Copper Development Association Inc.

Copper is the logical material for solar energy systems because:

- It has the best thermal conductivity of all engineering metals;
- It is highly resistant to both atmospheric and aqueous corrosion;
- It is easy to fabricate and to join by soldering or brazing;
- It has been used both for plumbing and for roofs since metals were first employed in those applications.

Copper's thermal advantages mean thinner copper sheet can collect the same heat as much thicker gages of aluminum or steel sheet, and copper collector tubes can be more widely spaced.

Copper's resistance to atmospheric corrosion is well demonstrated by its service in roofing and flashing. Unless attacked by the sulfur or nitrogen oxide exhausts from utilities or process industries, copper has withstood decades—even centuries—of weathering.

Copper resists hot water corrosion equally well. Properly sized to keep flow rates below those recommended on page 11, and properly installed, copper hot water systems are, for all practical purposes, completely resistant to corrosion.

The ease with which copper plumbing systems are joined by soldering needs no special emphasis. Sheet copper fabrication is equally recognized for its ease and simplicity.

General Considerations

It is not possible in a handbook of this type to cover all the variables a plumbing system designer may have to consider. However, in addition to the foregoing discussion, the following information may also prove helpful when preparing job specifications.

Expansion Loops—Copper tube, like all piping materials, expands and contracts with temperature changes. Therefore, in a copper tube system subjected to excessive temperature changes, a long line tends to buckle or bend when it expands unless compensation is built into the system. Severe stresses on the joints may also occur. Such stresses, buckles or bends are prevented by the use of expansion joints or by installing offsets, "U" bends, coil loops or similar arrangements in the tube assembly. These specially shaped tube segments take up expansion and contraction without excessive stress. The expansion of a length of copper tube may be calculated from the formula:

$$\begin{aligned} & \text{Temperature Rise (degrees F)} \\ & \times \text{Length (feet)} \\ & \times 12 \text{ (inches per foot)} \\ & \times \text{Expansion Coefficient (inches} \\ & \text{per inch per degree F)} \\ & = \text{Expansion (inches)} \end{aligned}$$

Calculation for expansion and contraction should be based on the average coefficient of expansion of copper which is 0.0000094 inch per inch per degree F, between 70°F and 212°F. For example, the expansion of each 100 feet of length of any size tube heated from room temperature (70°F) to 170°F (a 100°F rise) is 1.128 inches.

$$\begin{aligned} & 100^\circ\text{F} \times 100 \text{ ft} \times 12 \text{ in./ft.} \\ & \times 0.0000094 \text{ in./in./}^\circ\text{F} \\ & = 1.128 \text{ in.} \end{aligned}$$

Figure 3, page 34, shows the change in length per 100 feet of copper tube, with temperature. The previous example is shown by the dotted line.

Table 8, page 35, gives the radii necessary for coiled expansion loops, described in **Figure 4**, page 35. Expansion offset lengths may be estimated from **Table 8**.

Alternatively, the necessary length of tube in an expansion loop or offset can be calculated using the formula:

$$L = \frac{1}{12} \left(\frac{3E}{P} \right)^{1/2} (d_o e)^{1/2}$$

where:

- L = developed length, in feet, in the expansion loop or offset as shown in **Figure 4**.
- E = modulus of elasticity of copper, in psi.
- P = design allowable fiber stress of material in flexure, in psi.
- d_o = outside diameter of pipe, in inches.
- e = amount of expansion to be absorbed, in inches.

For annealed copper tube:

E = 17,000,000 psi

P = 6,000 psi

Thus, the developed length L is simply:

$$L = 7.68 (d_o e)^{1/2}$$

Tube Supports—Drawn temper tube, because of its rigidity, is preferred for exposed piping. Unless otherwise stated in plumbing codes, drawn temper tube requires support for horizontal lines at about 8-foot intervals for sizes of 1-inch and smaller, and at about 10-foot intervals for larger sizes.

Vertical lines are usually supported at every story or at about 10-foot intervals, but for long lines where there are the usual provisions for expansion and contraction, anchors may be several stories apart, provided there are sleeves or similar devices at all intermediate floors to restrain lateral movement, see **Figure 1**, page 13,

Annealed temper tube in coils permits long runs without intermediate joints. Vertical lines of annealed temper tube should be supported at least every 10 feet. Horizontal lines should be supported at least every 8 feet.

Resistance to Crushing—Tests made by placing a 3/4 -inch round steel bar at right angles across a 1-inch annealed copper tube and then exerting pressure downward revealed that, even with this severe point-contact loading, 700 pounds were required to crush the tube to 75 percent of its original diameter. Two-inch sizes, because of their greater wall thicknesses, resisted even more weight before crushing.

Plumbing codes and good piping practice require that all excavations shall be completely backfilled as soon after inspection as practical. Trenches should first be backfilled with 12 inches of tamped, clean earth which should not contain stones, cinders or other materials which would damage the tube or cause corrosion. Equipment such as bulldozers and graders may be used to complete backfilling. Suitable precautions should be taken to ensure permanent stability for tube laid in fresh ground fill.

Water Hammer—Water hammer is the term used to describe the destructive forces, pounding noises and vibrations which develop in a water system when the flowing liquid is stopped abruptly by a closing valve.

When water hammer occurs, a high-pressure shock wave reverberates within the piping system until the energy has been spent in frictional losses. The noise of such excessive pressure surges may be prevented by adding a capped air chamber or surge arresting device to the system.

Arresting devices are available

commercially to provide permanent protection against shock from water hammer. They are designed so the water in the system will not contact the air cushion in the arrester and, once installed, they require no further maintenance.

On single-fixture branch lines, the arrester should be placed immediately upstream from the fixture valve. On multiple-fixture branch lines, the preferred location for the arrester is on the branch line supplying the fixture group between the last two fixture supply pipes.

Collapse Pressure of Copper

Tube—The constantly increasing use of copper and copper alloy tube in condensers, water heaters and other heat transfer devices for water, gas and fluid lines, and many other engineering applications where a pressure differential exists on opposite sides of the tube wall, makes accurate data necessary regarding collapse pressures. See **Figure 2**, page 33.

Freezing—Annealed temper tube can withstand the expansion of freezing water several times before bursting. Under test, the water filling a 1/2-inch soft tube has been frozen as many as six times, and a 2-inch size, eleven times. This is a vital safety factor favoring soft tube for underground water services. However, it does not mean that copper water tube lines should be subjected to freezing.

Corrosion—Copper water tube is corrosion resistant. It is very infrequent that waters or special conditions are encountered which can be corrosive to copper tube. When they are encountered, they should be recognized and dealt with.

Since World War II, over 18 billion pounds of copper plumbing tube has been produced in the United States, 80% of which has been installed in water distribution systems. This translates into more than 7 million miles of copper tube. The rare problems of corrosion by aggressive water, possibly aggravated by faulty design or workmanship, should be viewed in the context of this total record of

outstanding service performance. In general, widespread use of copper plumbing tube in a locality can be taken as good evidence that the water there is not aggressive to copper.

When corrosion problems do occur they usually stem from one of the following causes:

- (1) aggressive, hard well waters that cause pitting;
- (2) soft, acidic waters that do not allow a protective film to form inside the copper tube;
- (3) system design or installation which results in excessive water flow velocity or turbulence in the tube;
- (4) unacceptable workmanship;
- (5) excessive or aggressive flux;
- (6) aggressive soil conditions.

Aggressive pitting waters can be identified by chemical analysis and treated to bring their composition within acceptable limits. Characteristically they have high total dissolved solids (t.d.s.) including sulfates and chlorides, a pH in the range of 7.2 to 7.8, a high content of carbon dioxide (CO₂) gas (over 10 parts per million, ppm), and the presence of dissolved oxygen (D.O.) gas.

A qualified water treatment professional can specify a treatment for any aggressive water to make it non-aggressive to plumbing materials. In general, this involves raising the pH and combining or eliminating the CO₂ gas. Sometimes simple aeration of the water, e.g., spraying in the open air, is treatment enough.

Pitting can also be caused or intensified by faulty workmanship which leaves excessive amounts of residual aggressive flux inside the tube after installation. If the joints have been overheated during installation and the excess residual flux has polymerized, the pitting problem can worsen.

Soft acidic waters can cause the annoying problem of green staining of fixtures or “green water.” Raising the pH of such waters to a value of about 7.2 or more usually solves the problem, but a qualified water treatment professional should be consulted. A typical treatment for an individual well water supply is to have the water flow through a bed of

marble or limestone chips.

Excessive water velocity causes erosion-corrosion or impingement attack in plumbing systems. As explained in the discussion of pressure system sizing beginning on page 10, to avoid erosion-corrosion (and noise) problems, the water velocity in a plumbing system should not exceed 5 to 8 feet per second—the lower limit applying to smaller tube sizes.

Velocity effects can be aggravated if the water is chemically aggressive due to pH or gas content as outlined above, or if solids (silt) are entrained in the flow. The combination of a velocity that is otherwise acceptable and a water chemistry that is somewhat aggressive can sometimes cause trouble that would not result from either factor by itself.

Erosion-corrosion can also be aggravated by faulty workmanship. For example, burrs left at cut tube ends can upset smooth water flow, cause localized turbulence and high flow velocities, resulting in erosion-corrosion.

Any metal pipe laid in cinders is subject to attack by the acid generated when sulfur compounds in the cinders combine with water. Under such circumstances, the tube should be isolated from the cinders with an inert moisture barrier, a wrapping of insulating tape, a coating of an asphaltum paint, or with some other approved material. With rare exception, natural soils do not attack copper.

Copper drainage tube rarely corrodes, except when misused or when errors have been made in designing or installing the drainage system. An improper horizontal slope can create a situation where corrosive solutions could lie in the tube and attack it. If hydrogen sulfide gas in large volume is allowed to vent back into the house drainage system, it can attack the tube.

Vibration—Copper tube can withstand the effects of vibration when careful consideration is given to the system design.

Care should be taken when installing systems subject to vibration

to assure that they are free from residual stresses due to bending or misalignment. Residual stresses coupled with vibration can cause fatigue at bends and connections where such residual stresses have been built into the system.

Durability—Under normal conditions, a correctly designed and properly installed copper water tube assembly will easily last the life of the building. And, throughout its existence, the assembly should function as well as it did when originally installed.

NSF Certification—The U.S. Safe Drinking Water Act (1996) and the Lead and Copper Rule (1991) require public water suppliers to provide non-corrosive drinking water to customers. Typically, this is accomplished through the use of pH adjustment (pH 6.5 to 8.5) and through the addition of corrosion inhibitors such as ortho- and

polyphosphates. The resultant tap water concentrations of lead and copper must be below the action levels of 15 μ g/L and 1300 μ g/L, respectively.

NSF International has certified several copper tube and fittings manufacturers to ANSI/NSF Standard 61. All have the limitations of being certified for use in non-corrosive aqueous environments. Specifically, the pH must not be below 6.5. Otherwise, resultant copper concentrations in tap water may exceed the action level established by the EPA.

ANSI/NSF Standard 61 requires products evaluated to conditions other than those specified in the standard (such as pH 5 and 10 exposure water) to be labeled with a limitation statement, as follows:

Copper tube (Alloy C12200) is Certified by NSF to ANSI/NSF Standard 61 for public water supplies

meeting or in the process of meeting the EPA Lead and Copper Rule (56FR 26460, June 7, 1991). Water supplies with pH less than 6.5 may require corrosion control to limit copper solubility in drinking water.

NSF Certified copper tube must bear the NSF Certification mark and the limitation statement. The length of the limitation statement makes it difficult to place on the tube itself. Additionally, current inking technology results in smearing and low legibility. For these reasons, NSF certification policies allow copper tube manufacturers to place the limitation statement on a tag attached to bundles of copper tube, or on the boxes of coiled copper tube. Placing “NSF” on the tube itself is still required.

TECHNICAL DATA



TABLE 1. Copper Tube: Types, Standards, Applications, Tempers, Lengths

Tube Type	Color Code	Standard	Application ¹	Commercially Available Lengths ²		
				Nominal or Standard Sizes	Drawn	Annealed
TYPE K	Green	ASTM B 88 ³	Domestic Water Service and Distribution, Fire Protection, Solar, Fuel/Fuel Oil, HVAC, Snow Melting, Compressed Air, Natural Gas, Liquefied Petroleum (LP) Gas, Vacuum	STRAIGHT LENGTHS:		
				1/4-inch to 8-inch	20 ft	20 ft
				10-inch	18 ft	18 ft
				12-inch	12 ft	12 ft
				COILS:		
				1/4-inch to 1-inch	—	60 ft
				1 1/4 inch and 1 1/2-inch	—	100 ft
TYPE L	Blue	ASTM B 88	Domestic Water Service and Distribution, Fire Protection, Solar, Fuel/Fuel Oil, Natural Gas, Liquefied Petroleum (LP) Gas, HVAC, Snow Melting, Compressed Air, Vacuum	STRAIGHT LENGTHS:		
				1/4-inch to 10-inch	20 ft	20 ft
				12-inch	18 ft	18 ft
				COILS:		
				1/4-inch to 1-inch	—	60 ft
				1 1/4 inch and 1 1/2-inch	—	100 ft
				2-inch	—	60 ft
TYPE M	Red	ASTM B 88	Domestic Water Service and Distribution, Fire Protection, Solar, Fuel/Fuel Oil, HVAC, Snow Melting, Vacuum	STRAIGHT LENGTHS:		
				1/4-inch to 12-inch	20 ft	N/A
DWW	Yellow	ASTM B 306	Drain, Waste, Vent, HVAC, Solar	STRAIGHT LENGTHS:		
				1 1/4-inch to 8-inch	20 ft	N/A
ACR	Blue	ASTM B 280	Air Conditioning, Refrigeration, Natural Gas, Liquefied Petroleum (LP) Gas, Compressed Air	STRAIGHT LENGTHS:		
				3/8-inch to 4 1/8-inch	20 ft	⁴
				COILS:		
OXY, MED, OXY/MED, OXY/ACR, ACR/MED	(K)Green (L)Blue	ASTM B 819	Medical Gas Compressed Medical Air, Vacuum	STRAIGHT LENGTHS:		
				1/4-inch to 8-inch	20 ft	N/A

¹ There are many other copper and copper alloy tubes and pipes available for specialized applications. For information on these products, contact the Copper Development Association Inc.

² Individual manufacturers may have commercially available lengths in addition to those shown in this table.

³ Tube made to other ASTM standards is also intended for plumbing applications, although ASTM B 88 is by far the most widely used. ASTM Standard Classification B 698 lists six plumbing tube standards including B 88.

⁴ Available as special order only.

TABLE 2a. Dimensions and Physical Characteristics of Copper Tube: TYPE K

Nominal or Standard Size, inches	Nominal Dimensions, inches			Calculated Values (based on nominal dimensions)				
	Outside Diameter	Inside Diameter	Wall Thickness	Cross Sectional Area of Bore, sq inches	Weight of Tube Only, pounds per linear ft	Weight of Tube & Water, pounds per linear ft	Contents of Tube per linear ft	
							Cu ft	Gal
1/4	.375	.305	.035	.073	.145	.177	.00051	.00379
3/8	.500	.402	.049	.127	.269	.324	.00088	.00660
1/2	.625	.527	.049	.218	.344	.438	.00151	.0113
5/8	.750	.652	.049	.334	.418	.562	.00232	.0174
3/4	.875	.745	.065	.436	.641	.829	.00303	.0227
1	1.125	.995	.065	.778	.839	1.18	.00540	.0404
1 1/4	1.375	1.245	.065	1.22	1.04	1.57	.00847	.0634
1 1/2	1.625	1.481	.072	1.72	1.36	2.10	.0119	.0894
2	2.125	1.959	.083	3.01	2.06	3.36	.0209	.156
2 1/2	2.625	2.435	.095	4.66	2.93	4.94	.0324	.242
3	3.125	2.907	.109	6.64	4.00	6.87	.0461	.345
3 1/2	3.625	3.385	.120	9.00	5.12	9.01	.0625	.468
4	4.125	3.857	.134	11.7	6.51	11.6	.0813	.608
5	5.125	4.805	.160	18.1	9.67	17.5	.126	.940
6	6.125	5.741	.192	25.9	13.9	25.1	.180	1.35
8	8.125	7.583	.271	45.2	25.9	45.4	.314	2.35
10	10.125	9.449	.338	70.1	40.3	70.6	.487	3.64
12	12.125	11.315	.405	101	57.8	101	.701	5.25

TABLE 2b. Dimensions and Physical Characteristics of Copper Tube: TYPE L

Nominal or Standard Size, inches	Nominal Dimensions, inches			Calculated Values (based on nominal dimensions)				
	Outside Diameter	Inside Diameter	Wall Thickness	Cross Sectional Area of Bore, sq inches	Weight of Tube Only, pounds per linear ft	Weight of Tube & Water, pounds per linear ft	Contents of Tube per linear ft	
							Cu ft	Gal
1/4	.375	.315	.030	.078	.126	.160	.00054	.00405
3/8	.500	.430	.035	.145	.198	.261	.00101	.00753
1/2	.625	.545	.040	.233	.285	.386	.00162	.0121
5/8	.750	.666	.042	.348	.362	.506	.00232	.0174
3/4	.875	.785	.045	.484	.455	.664	.00336	.0251
1	1.125	1.025	.050	.825	.655	1.01	.00573	.0429
1 1/4	1.375	1.265	.055	1.26	.884	1.43	.00875	.0655
1 1/2	1.625	1.505	.060	1.78	1.14	1.91	.0124	.0925
2	2.125	1.985	.070	3.09	1.75	3.09	.0215	.161
2 1/2	2.625	2.465	.080	4.77	2.48	4.54	.0331	.248
3	3.125	2.945	.090	6.81	3.33	6.27	.0473	.354
3 1/2	3.625	3.425	.100	9.21	4.29	8.27	.0640	.478
4	4.125	3.905	.110	12.0	5.38	10.1	.0764	.571
5	5.125	4.875	.125	18.7	7.61	15.7	.130	.971
6	6.125	5.845	.140	26.8	10.2	21.8	.186	1.39
8	8.125	7.725	.200	46.9	19.3	39.6	.326	2.44
10	10.125	9.625	.250	72.8	30.1	61.6	.506	3.78
12	12.125	11.565	.280	105	40.4	85.8	.729	5.45

TABLE 2c. Dimensions and Physical Characteristics of Copper Tube: TYPE M

Nominal or Standard Size, inches	Nominal Dimensions, inches			Calculated Values (based on nominal dimensions)				
	Outside Diameter	Inside Diameter	Wall Thickness	Cross Sectional Area of Bore, sq inches	Weight of Tube Only, pounds per linear ft	Weight of Tube & Water, pounds per linear ft	Contents of Tube per linear ft	
							Cu ft	Gal
3/8	.500	.450	.025	.159	.145	.214	.00110	.00826
1/2	.625	.569	.028	.254	.204	.314	.00176	.0132
3/4	.875	.811	.032	.517	.328	.551	.00359	.0269
1	1.125	1.055	.035	.874	.465	.843	.00607	.0454
1 1/4	1.375	1.291	.042	1.31	.682	1.25	.00910	.0681
1 1/2	1.625	1.527	.049	1.83	.940	1.73	.0127	.0951
2	2.125	2.009	.058	3.17	1.46	2.83	.0220	.165
2 1/2	2.625	2.495	.065	4.89	2.03	4.14	.0340	.254
3	3.125	2.981	.072	6.98	2.68	5.70	.0485	.363
3 1/2	3.625	3.459	.083	9.40	3.58	7.64	.0653	.488
4	4.125	3.935	.095	12.2	4.66	9.83	.0847	.634
5	5.125	4.907	.109	18.9	6.66	14.8	.131	.982
6	6.125	5.881	.122	27.2	8.92	20.7	.189	1.41
8	8.125	7.785	.170	47.6	16.5	37.1	.331	2.47
10	10.125	9.701	.212	73.9	25.6	57.5	.513	3.84
12	12.125	11.617	.254	106	36.7	82.5	.736	5.51

TABLE 2d. Dimensions and Physical Characteristics of Copper Tube: DWV (Drain, Waste and Vent)

Nominal or Standard Size, inches	Nominal Dimensions, inches			Calculated Values (based on nominal dimensions)				
	Outside Diameter	Inside Diameter	Wall Thickness	Cross Sectional Area of Bore, sq inches	Weight of Tube Only, pounds per linear ft	Weight of Tube & Water, pounds per linear ft	Contents of Tube per linear ft	
							Cu ft	Gal
1 1/4	1.375	1.295	.040	1.32	.650	1.22	.00917	.0686
1 1/2	1.625	1.541	.042	1.87	.809	1.62	.0130	.0971
2	2.125	2.041	.042	3.27	1.07	2.48	.0227	.170
3	3.125	3.030	.045	7.21	1.69	4.81	.0501	.375
4	4.125	4.009	.058	11.6	2.87	7.88	.0806	.603
5	5.125	4.981	.072	19.5	4.43	12.9	.135	1.01
6	6.125	5.959	.083	27.9	6.10	18.2	.194	1.45
8	8.125	7.907	.109	49.1	10.6	31.8	.341	2.55

**TABLE 2e. Dimensions and Physical Characteristics of Copper Tube: ACR (Air-Conditioning and Refrigeration Field Service)
(A= Annealed Temper, D=Drawn Temper)**

Nominal or Standard Size, inches		Nominal Dimensions, inches			Calculated Values (based on nominal dimensions)				
		Outside Diameter	Inside Diameter	Wall Thickness	Cross Sectional Area of Bore, sq inches	External Surface, sq ft per linear ft	Internal Surface, sq ft per linear ft	Weight of Tube Only, pounds per linear ft	Contents of Tube, cu ft per linear ft
1/8	A	.125	.065	.030	.00332	.0327	.0170	.0347	.00002
3/16	A	.187	.128	.030	.0129	.0492	.0335	.0575	.00009
1/4	A	.250	.190	.030	.0284	.0655	.0497	.0804	.00020
5/16	A	.312	.248	.032	.0483	.0817	.0649	.109	.00034
3/8	A	.375	.311	.032	.076	.0982	.0814	.134	.00053
	D	.375	.315	.030	.078	.0982	.0821	.126	.00054
1/2	A	.500	.436	.032	.149	.131	.114	.182	.00103
	D	.500	.430	.035	.145	.131	.113	.198	.00101
5/8	A	.625	.555	.035	.242	.164	.145	.251	.00168
	D	.625	.545	.040	.233	.164	.143	.285	.00162
3/4	A	.750	.680	.035	.363	.196	.178	.305	.00252
	A	.750	.666	.042	.348	.196	.174	.362	.00242
	D	.750	.666	.042	.348	.196	.174	.362	.00242
7/8	A	.875	.785	.045	.484	.229	.206	.455	.00336
	D	.875	.785	.045	.484	.229	.206	.455	.00336
1 1/8	A	1.125	1.025	.050	.825	.294	.268	.655	.00573
	D	1.125	1.025	.050	.825	.294	.268	.655	.00573
1 3/8	A	1.375	1.265	.055	1.26	.360	.331	.884	.00875
	D	1.375	1.265	.055	1.26	.360	.331	.884	.00875
1 5/8	A	1.625	1.505	.060	1.78	.425	.394	1.14	.0124
	D	1.625	1.505	.060	1.78	.425	.394	1.14	.0124
2 1/8	D	2.125	1.985	.070	3.09	.556	.520	1.75	.0215
2 5/8	D	2.625	2.465	.080	4.77	.687	.645	2.48	.0331
3 1/8	D	3.125	2.945	.090	6.81	.818	.771	3.33	.0473
3 5/8	D	3.625	3.425	.100	9.21	.949	.897	4.29	.0640
4 1/8	D	4.125	3.905	.110	12.0	1.08	1.02	5.38	.0833

TABLE 2f. Dimensions and Physical Characteristics of Copper Tube: Medical Gas, K and L

Nominal or Standard Size, inches	Nominal Dimensions, inches			Calculated Values (based on nominal dimensions)				
	Outside Diameter	Inside Diameter	Wall Thickness	Cross Sectional Area of Bore, sq inches	Internal surface, sq feet per linear ft	Weight of Tube Only, pounds per linear ft	Contents of Tube, cu feet per linear ft	
1/4	K	.375	.305	.035	.073	.0789	.145	.00051
	L	.375	.315	.030	.078	.0825	.126	.00054
3/8	K	.500	.402	.049	.127	.105	.269	.00088
	L	.500	.430	.035	.145	.113	.198	.00101
1/2	K	.625	.527	.049	.218	.130	.344	.00151
	L	.625	.545	.040	.233	.143	.285	.00162
5/8	K	.750	.652	.049	.334	.171	.418	.00232
	L	.750	.666	.042	.348	.174	.362	.00242
3/4	K	.875	.745	.065	.436	.195	.641	.00303
	L	.875	.785	.045	.484	.206	.455	.00336
1	K	1.125	.995	.065	.778	.261	.839	.00540
	L	1.125	1.025	.050	.825	.268	.655	.00573
1 1/4	K	1.375	1.245	.065	1.222	.326	1.04	.00845
	L	1.375	1.265	.055	1.26	.331	.884	.00873
1 1/2	K	1.625	1.481	.072	1.72	.388	1.36	.0120
	L	1.625	1.505	.060	1.78	.394	1.14	.0124
2	K	2.125	1.959	.083	3.01	.522	2.06	.0209
	L	2.125	1.985	.070	3.09	.520	1.75	.0215
2 1/2	K	2.625	2.435	.095	4.66	.638	2.93	.0323
	L	2.625	2.465	.080	4.77	.645	2.48	.0331
3	K	3.125	2.907	.109	6.64	.761	4.00	.0461
	L	3.125	2.945	.090	6.81	.761	3.33	.0473
3 1/2	K	3.625	3.385	.120	9.00	.886	5.12	.0625
	L	3.625	3.425	.100	9.21	.897	4.29	.0640
4	K	4.125	3.857	.134	11.7	1.01	6.51	.0811
	L	4.125	3.905	.110	12.0	1.02	5.38	.0832
5	K	5.125	4.805	.160	18.1	1.26	9.67	.126
	L	5.125	4.875	.125	18.7	1.28	7.61	.130
6	K	6.125	5.741	.192	25.9	1.50	13.9	.180
	L	6.125	5.854	.140	26.8	1.53	10.2	.186
8	K	8.125	7.583	.271	45.2	1.99	25.9	.314
	L	8.125	7.725	.200	46.9	2.02	19.3	.325

TABLE 3a. Rated Internal Working Pressures for Copper Tube: TYPE K*

Nominal Size, in	Annealed							Drawn**						
	S= 6000 psi 100 F	S= 5100 psi 150 F	S= 4900 psi 200 F	S= 4800 psi 250 F	S= 4700 psi 300 F	S= 4000 psi 350 F	S= 3000 psi 400 F	S= 10,300 psi 100 F	S= 10,300 psi 150 F	S= 10,300 psi 200 F	S= 10,300 psi 250 F	S= 10,000 psi 300 F	S= 9,700 psi 350 F	S= 9,400 psi 400 F
1/4	1074	913	877	860	842	716	537	1850	1850	1850	1850	1796	1742	1688
3/8	1130	960	923	904	885	753	565	1946	1946	1946	1946	1889	1833	1776
1/2	891	758	728	713	698	594	446	1534	1534	1534	1534	1490	1445	1400
5/8	736	626	601	589	577	491	368	1266	1266	1266	1266	1229	1193	1156
3/4	852	724	696	682	668	568	426	1466	1466	1466	1466	1424	1381	1338
1	655	557	535	524	513	437	327	1126	1126	1126	1126	1093	1061	1028
1 1/4	532	452	434	425	416	354	266	914	914	914	914	888	861	834
1 1/2	494	420	404	396	387	330	247	850	850	850	850	825	801	776
2	435	370	355	348	341	290	217	747	747	747	747	726	704	682
2 1/2	398	338	325	319	312	265	199	684	684	684	684	664	644	624
3	385	328	315	308	302	257	193	662	662	662	662	643	624	604
3 1/2	366	311	299	293	286	244	183	628	628	628	628	610	592	573
4	360	306	294	288	282	240	180	618	618	618	618	600	582	564
5	345	293	281	276	270	230	172	592	592	592	592	575	557	540
6	346	295	283	277	271	231	173	595	595	595	595	578	560	543
8	369	314	301	295	289	246	184	634	634	634	634	615	597	578
10	369	314	301	295	289	246	184	634	634	634	634	615	597	578
12	370	314	302	296	290	247	185	635	635	635	635	617	598	580

TABLE 3b. Rated Internal Working Pressure for Copper Tube: TYPE L*

Nominal Size, in	Annealed							Drawn**						
	S= 6000 psi 100 F	S= 5100 psi 150 F	S= 4900 psi 200 F	S= 4800 psi 250 F	S= 4700 psi 300 F	S= 4000 psi 350 F	S= 3000 psi 400 F	S= 10,300 psi 100 F	S= 10,300 psi 150 F	S= 10,300 psi 200 F	S= 10,300 psi 250 F	S= 10,000 psi 300 F	S= 9,700 psi 350 F	S= 9,400 psi 400 F
1/4	912	775	745	729	714	608	456	1569	1569	1569	1569	1524	1478	1432
3/8	779	662	636	623	610	519	389	1341	1341	1341	1341	1302	1263	1224
1/2	722	613	589	577	565	481	361	1242	1242	1242	1242	1206	1169	1133
5/8	631	537	516	505	495	421	316	1086	1086	1086	1086	1055	1023	991
3/4	582	495	475	466	456	388	291	1002	1002	1002	1002	972	943	914
1	494	420	404	395	387	330	247	850	850	850	850	825	801	776
1 1/4	439	373	358	351	344	293	219	755	755	755	755	733	711	689
1 1/2	408	347	334	327	320	272	204	702	702	702	702	682	661	641
2	364	309	297	291	285	242	182	625	625	625	625	607	589	570
2 1/2	336	285	274	269	263	224	168	577	577	577	577	560	544	527
3	317	270	259	254	248	211	159	545	545	545	545	529	513	497
3 1/2	304	258	248	243	238	202	152	522	522	522	522	506	491	476
4	293	249	240	235	230	196	147	504	504	504	504	489	474	460
5	269	229	220	215	211	179	135	462	462	462	462	449	435	422
6	251	213	205	201	196	167	125	431	431	431	431	418	406	393
8	270	230	221	216	212	180	135	464	464	464	464	451	437	424
10	271	231	222	217	212	181	136	466	466	466	466	452	439	425
12	253	215	207	203	199	169	127	435	435	435	435	423	410	397

NOTE: *Based on maximum allowable stress in tension (psi) for the indicated temperatures (°F), see page 12.

**When brazing or welding is used to join drawn tube, the corresponding annealed rating must be used, see page 12.

TABLE 3c. Rated Internal Working Pressure for Copper Tube: TYPE M*

Nominal Size, in	Annealed***							Drawn**						
	S= 6000 psi 100 F	S= 5100 psi 150 F	S= 4900 psi 200 F	S= 4800 psi 250 F	S= 4700 psi 300 F	S= 4000 psi 350 F	S= 3000 psi 400 F	S= 10,300 psi 100 F	S= 10,300 psi 150 F	S= 10,300 psi 200 F	S= 10,300 psi 250 F	S= 10,000 psi 300 F	S= 9,700 psi 350 F	S= 9,400 psi 400 F
1/4	—	—	—	—	—	—	—	—	—	—	—	—	—	—
3/8	570	485	466	456	447	380	285	982	982	982	982	953	925	896
1/2	494	420	403	395	387	329	247	850	850	850	850	825	800	776
5/8	—	—	—	—	—	—	—	—	—	—	—	—	—	—
3/4	407	346	332	326	319	271	204	701	701	701	701	680	660	639
1	337	286	275	270	264	225	169	580	580	580	580	563	546	529
1 1/4	338	287	276	271	265	225	169	582	582	582	582	565	548	531
1 1/2	331	282	270	265	259	221	166	569	569	569	569	553	536	520
2	299	254	244	239	234	199	149	514	514	514	514	499	484	469
2 1/2	274	233	224	219	215	183	137	471	471	471	471	457	444	430
3	253	215	207	203	199	169	127	435	435	435	435	423	410	397
3 1/2	252	214	206	202	197	168	126	433	433	433	433	421	408	395
4	251	213	205	201	197	167	126	431	431	431	431	419	406	394
5	233	198	190	186	182	155	116	400	400	400	400	388	377	365
6	218	186	178	175	171	146	109	375	375	375	375	364	353	342
8	229	195	187	183	180	153	115	394	394	394	394	382	371	359
10	230	195	188	184	180	153	115	394	394	394	394	383	371	360
12	230	195	188	184	180	153	115	395	395	395	395	383	372	360

TABLE 3d. Rated Internal Working Pressure for Copper Tube: DWV*

Nominal Size, in	Annealed***							Drawn**						
	S= 6000 psi 100 F	S= 5100 psi 150 F	S= 4900 psi 200 F	S= 4800 psi 250 F	S= 4700 psi 300 F	S= 4000 psi 350 F	S= 3000 psi 400 F	S= 10,300 psi 100 F	S= 10,300 psi 150 F	S= 10,300 psi 200 F	S= 10,300 psi 250 F	S= 10,000 psi 300 F	S= 9,700 psi 350 F	S= 9,400 psi 400 F
1/4	330	280	269	264	258	220	165	566	566	566	566	549	533	516
1/2	293	249	240	235	230	196	147	503	503	503	503	489	474	459
2	217	185	178	174	170	145	109	373	373	373	373	362	352	341
3	159	135	130	127	125	106	80	273	273	273	273	265	257	249
4	150	127	122	120	117	100	75	257	257	257	257	250	242	235
5	151	129	124	121	119	101	76	260	260	260	260	252	245	237
6	148	126	121	119	116	99	74	255	255	255	255	247	240	232
8	146	124	119	117	114	97	73	251	251	251	251	244	236	229

NOTE: *Based on maximum allowable stress in tension (psi) for the indicated temperatures (°F), see page 12.

**When brazing or welding is used to join drawn tube, the corresponding annealed rating must be used, see page 12.

***Types M and DWV are not normally available in the annealed temper. Shaded values are provided for guidance when drawn temper tube is brazed or welded, see page 12.

TABLE 3e. Rated Internal Working Pressure for Copper Tube: ACR* (Air Conditioning and Refrigeration Field Service)

Tube Size (OD), in	Annealed							Drawn**						
	COILS													
	S= 6000 psi 100 F	S= 5100 psi 150 F	S= 4900 psi 200 F	S= 4800 psi 250 F	S= 4700 psi 300 F	S= 4000 psi 350 F	S= 3000 psi 400 F	S= 10,300 psi 100 F	S= 10,300 psi 150 F	S= 10,300 psi 200 F	S= 10,300 psi 250 F	S= 10,000 psi 300 F	S= 9,700 psi 350 F	S= 9,400 psi 400 F
1/8	3074	2613	2510	2459	2408	2049	1537	—	—	—	—	—	—	—
3/16	1935	1645	1581	1548	1516	1290	968	—	—	—	—	—	—	—
1/4	1406	1195	1148	1125	1102	938	703	—	—	—	—	—	—	—
5/16	1197	1017	977	957	937	798	598	—	—	—	—	—	—	—
3/8	984	836	803	787	770	656	492	—	—	—	—	—	—	—
1/2	727	618	594	581	569	485	363	—	—	—	—	—	—	—
5/8	618	525	504	494	484	412	309	—	—	—	—	—	—	—
3/4	511	435	417	409	400	341	256	—	—	—	—	—	—	—
3/4	631	537	516	505	495	421	316	—	—	—	—	—	—	—
7/8	582	495	475	466	456	388	291	—	—	—	—	—	—	—
1 1/8	494	420	404	395	387	330	247	—	—	—	—	—	—	—
1 3/8	439	373	358	351	344	293	219	—	—	—	—	—	—	—
1 5/8	408	347	334	327	320	272	204	—	—	—	—	—	—	—
	STRAIGHT LENGTHS													
	S= 6000 psi 100 F	S= 5100 psi 150 F	S= 4900 psi 200 F	S= 4800 psi 250 F	S= 4700 psi 300 F	S= 4000 psi 350 F	S= 3000 psi 400 F	S= 10,300 psi 100 F	S= 10,300 psi 150 F	S= 10,300 psi 200 F	S= 10,300 psi 250 F	S= 10,000 psi 300 F	S= 9,700 psi 350 F	S= 9,400 psi 400 F
3/8	914	777	747	731	716	609	457	1569	1569	1569	1569	1524	1478	1432
1/2	781	664	638	625	612	521	391	1341	1341	1341	1341	1302	1263	1224
5/8	723	615	591	579	567	482	362	1242	1242	1242	1242	1206	1169	1133
3/4	633	538	517	506	496	422	316	1086	1086	1086	1086	1055	1023	991
7/8	583	496	477	467	457	389	292	1002	1002	1002	1002	972	943	914
1 1/8	495	421	404	396	388	330	248	850	850	850	850	825	801	776
1 3/8	440	374	359	352	344	293	220	755	755	755	755	733	711	689
1 5/8	409	348	334	327	320	273	205	702	702	702	702	682	661	641
2 1/8	364	309	297	291	285	243	182	625	625	625	625	607	589	570
2 5/8	336	286	275	269	263	224	168	577	577	577	577	560	544	527
3 1/8	317	270	259	254	249	212	159	545	545	545	545	529	513	497
3 5/8	304	258	248	243	238	203	152	522	522	522	522	506	491	476
4 1/8	293	249	240	235	230	196	147	504	504	504	504	489	474	460

NOT MANUFACTURED

NOTE: *Based on maximum allowable stress in tension (psi) for the indicated temperatures (°F), see page 12.
 **When brazing or welding is used to join drawn tube, the corresponding annealed rating must be used, see page 12.

TABLE 4. Pressure-Temperature Ratings of Soldered and Brazed Joints

Joining Material ⁽⁴⁾	Service Temperature, °F	Fitting Type	Maximum Working Gage Pressure (psi), for Standard Water Tube Sizes ⁽¹⁾				
			Nominal of Standard Size, inches				
			1/8 through 1	1 1/4 through 2	2 1/2 through 4	5 through 8	10 through 12
Alloy Sn50 50-50 Tin-Lead Solder ⁽⁵⁾	100	Pressure ⁽²⁾	200	175	150	135	100
		DWV ⁽³⁾	—	95	80	70	—
	150	Pressure ⁽²⁾	150	125	100	90	70
		DWV ⁽³⁾	—	70	55	45	—
	200	Pressure ⁽²⁾	100	90	75	70	50
		DWV ⁽³⁾	—	50	40	35	—
	250	Pressure ⁽²⁾	85	75	50	45	40
		DWV ⁽³⁾	—	—	—	—	—
	Saturated Steam	Pressure	15	15	15	15	15
	Alloy Sb5 95-5 Tin-Antimony Solder	100	Pressure ⁽²⁾	1090	850	705	660
DWV ⁽³⁾			—	390	325	330	—
150		Pressure ⁽²⁾	625	485	405	375	285
		DWV ⁽³⁾	—	225	185	190	—
200		Pressure ⁽²⁾	505	395	325	305	230
		DWV ⁽³⁾	—	180	150	155	—
250		Pressure ⁽²⁾	270	210	175	165	125
		DWV ⁽³⁾	—	95	80	80	—
Saturated Steam		Pressure	15	15	15	15	15
Alloy E		100	Pressure ⁽²⁾	710	555	460	430
	DWV ⁽³⁾		—	255	210	215	—
	150	Pressure ⁽²⁾	475	370	305	285	215
		DWV ⁽³⁾	—	170	140	140	—
	200	Pressure ⁽²⁾	375	290	240	225	170
		DWV ⁽³⁾	—	135	110	115	—
	250	Pressure ⁽²⁾	320	250	205	195	145
		DWV ⁽³⁾	—	115	95	95	—
	Saturated Steam	Pressure	15	15	15	15	15
	Alloy HB	100	Pressure ⁽²⁾	1035	805	670	625
DWV ⁽³⁾			—	370	310	315	—
150		Pressure ⁽²⁾	710	555	460	430	325
		DWV ⁽³⁾	—	255	210	215	—
200		Pressure ⁽²⁾	440	345	285	265	200
		DWV ⁽³⁾	—	155	130	135	—
250		Pressure ⁽²⁾	430	335	275	260	195
		DWV ⁽³⁾	—	155	125	130	—
Saturated Steam		Pressure	15	15	15	15	15
Joining materials melting at or above 1100° F ⁽⁶⁾		Pressure-temperature ratings consistent with the materials and procedures employed (see Table 3, Annealed).					
	Saturated Steam	Pressure	120	120	120	120	120

NOTE: For extremely low working temperatures in the 0°F to minus 200°F range, it is recommended that a joint material melting at or above 1100°F be employed (see Note ⁽⁶⁾).

⁽¹⁾ Standard water tube sizes per ASTM B 88.

⁽²⁾ Ratings up to 8 inches in size are those given in ASME B16.22 *Wrought Copper and Copper Alloy Solder Joint Pressure Fittings* and ASME B16.18 *Cast Copper and Copper Alloy Solder Joint Fittings*. Rating for 10- to 12-inch sizes are those given in ASME B16.18 *Cast Copper and Copper Alloy Solder Joint Pressure Fittings*.

⁽³⁾ Using ASME B16.29 *Wrought Copper and Wrought Copper Alloy Solder Joint Drainage Fittings — DWV*, and ASME B16.23 *Cast Copper Alloy Solder Joint Drainage Fittings — DWV*.

⁽⁴⁾ Alloy designations are per ASTM B 32.

⁽⁵⁾ The Safe Drinking Water Act Amendment of 1986 prohibits the use in potable water systems of any solder having a lead content in excess of 0.2%.

⁽⁶⁾ These joining materials are defined as *brazing alloys* by the American Welding Society.

TABLE 5. Actual Burst Pressures,¹ Types K, L, and M Copper Water Tube, psi at Room Temperature

Nominal or Standard Size, inches	Actual Outside Diameter, in	K		L ²		M	
		Drawn	Annealed	Drawn	Annealed	Drawn	Annealed
1/2	5/8	9840	4535	7765	3885	6135	—
3/4	7/8	9300	4200	5900	2935	4715	—
1	1 1/8	7200	3415	5115	2650	3865	—
1 1/4	1 3/8	5525	2800	4550	2400	3875	—
1 1/2	1 5/8	5000	2600	4100	2200	3550	—
2	2 1/8	3915	2235	3365	1910	2935	—
2 1/2	2 5/8	3575	—	3215	—	2800	—
3	3 1/8	3450	—	2865	—	2665	—
4	4 1/8	3415	—	2865	—	2215	—
5	5 1/8	3585	—	2985	—	2490	—
6	6 1/8	3425	—	2690	—	2000	—
8	8 1/8	3635	—	2650	—	2285	—

¹ The figures shown are averages of three certified tests performed on each type and size of water tube. In each case, wall thickness was at or near the minimum prescribed for each tube type. No burst pressure in any test deviated from the average by more than 5 percent.

² These burst pressures can be used for ACR tube of equivalent actual O.D. and wall thickness.

TABLE 6. Pressure Loss of Water Due to Friction in Types K, L and M Copper Tube (psi per linear foot of tube)

FLOW, GPM	NOMINAL OR STANDARD SIZE, INCHES																							
	1/4			3/8			1/2			3/4			1			1 1/4			1 1/2			2		
	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M
1	<i>0.138</i>	<i>0.118</i>	N/A	<i>0.036</i>	<i>0.023</i>	<i>0.021</i>	<i>0.010</i>	<i>0.008</i>	<i>0.007</i>	<i>0.002</i>	<i>0.001</i>	<i>0.001</i>	<i>0.000</i>											
2			N/A	<i>0.130</i>	<i>0.084</i>	<i>0.075</i>	<i>0.035</i>	<i>0.030</i>	<i>0.024</i>	<i>0.006</i>	<i>0.005</i>	<i>0.004</i>	<i>0.002</i>	<i>0.001</i>	<i>0.003</i>	<i>0.001</i>	<i>0.000</i>							
3			N/A	<i>0.275</i>	<i>0.177</i>	<i>0.159</i>	<i>0.074</i>	<i>0.062</i>	<i>0.051</i>	<i>0.014</i>	<i>0.011</i>	<i>0.009</i>	<i>0.003</i>	<i>0.003</i>	<i>0.001</i>	<i>0.001</i>	<i>0.001</i>	<i>0.001</i>	<i>0.000</i>	<i>0.000</i>	<i>0.000</i>	<i>0.000</i>	<i>0.000</i>	<i>0.000</i>
4			N/A				<i>0.125</i>	<i>0.106</i>	<i>0.086</i>	<i>0.023</i>	<i>0.018</i>	<i>0.015</i>	<i>0.006</i>	<i>0.005</i>	<i>0.004</i>	<i>0.002</i>	<i>0.002</i>	<i>0.002</i>	<i>0.001</i>	<i>0.001</i>	<i>0.001</i>	<i>0.000</i>	<i>0.000</i>	<i>0.000</i>
5			N/A				<i>0.189</i>	<i>0.161</i>	<i>0.130</i>	<i>0.035</i>	<i>0.027</i>	<i>0.023</i>	<i>0.009</i>	<i>0.007</i>	<i>0.006</i>	<i>0.003</i>	<i>0.003</i>	<i>0.002</i>	<i>0.001</i>	<i>0.001</i>	<i>0.001</i>	<i>0.000</i>	<i>0.000</i>	<i>0.000</i>
10			N/A							<i>0.126</i>	<i>0.098</i>	<i>0.084</i>	<i>0.031</i>	<i>0.027</i>	<i>0.023</i>	<i>0.010</i>	<i>0.010</i>	<i>0.009</i>	<i>0.004</i>	<i>0.004</i>	<i>0.004</i>	<i>0.001</i>	<i>0.001</i>	<i>0.001</i>
15			N/A										<i>0.065</i>	<i>0.057</i>	<i>0.049</i>	<i>0.022</i>	<i>0.020</i>	<i>0.018</i>	<i>0.009</i>	<i>0.009</i>	<i>0.008</i>	<i>0.002</i>	<i>0.002</i>	<i>0.002</i>
20			N/A										<i>0.096</i>	<i>0.084</i>		<i>0.037</i>	<i>0.035</i>	<i>0.031</i>	<i>0.016</i>	<i>0.015</i>	<i>0.014</i>	<i>0.004</i>	<i>0.004</i>	<i>0.004</i>
25			N/A													<i>0.057</i>	<i>0.052</i>	<i>0.047</i>	<i>0.024</i>	<i>0.022</i>	<i>0.021</i>	<i>0.006</i>	<i>0.006</i>	<i>0.005</i>
30			N/A													<i>0.079</i>	<i>0.073</i>	<i>0.066</i>	<i>0.034</i>	<i>0.031</i>	<i>0.029</i>	<i>0.009</i>	<i>0.008</i>	<i>0.008</i>
35			N/A																<i>0.045</i>	<i>0.042</i>	<i>0.039</i>	<i>0.012</i>	<i>0.011</i>	<i>0.010</i>
40			N/A																<i>0.058</i>	<i>0.054</i>	<i>0.050</i>	<i>0.015</i>	<i>0.014</i>	<i>0.013</i>
45			N/A																	<i>0.062</i>		<i>0.018</i>	<i>0.017</i>	<i>0.016</i>
50			N/A																			<i>0.022</i>	<i>0.021</i>	<i>0.020</i>
60			N/A																			<i>0.031</i>	<i>0.029</i>	<i>0.028</i>
70			N/A																			<i>0.042</i>	<i>0.039</i>	<i>0.037</i>
80			N/A																					
90			N/A																					
100			N/A																					
120			N/A																					
140			N/A																					
160			N/A																					
180			N/A																					
200			N/A																					
250			N/A																					
300			N/A																					
350			N/A																					
400			N/A																					
450			N/A																					
500			N/A																					
550			N/A																					
600			N/A																					
650			N/A																					
700			N/A																					
760			N/A																					
1000			N/A																					
2000			N/A																					

NOTES:

1. Fluid velocities in excess of 5-8 feet per second are not recommended.
2. Friction loss values shown are for the flow rates that do not exceed a velocity of 8 feet per second.
3. Highlighted and italicized friction loss values indicate flow rates that are between 5 feet and 8 feet per second.

FLOW, GPM	NOMINAL OR STANDARD SIZE, INCHES																							
	2 1/2			3			4			5			6			8			10			12		
	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M	K	L	M
1	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
2	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
3	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
4	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
5	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
10	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
15	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
20	0.001	0.001	0.001	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
25	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
30	0.003	0.003	0.003	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
35	0.004	0.004	0.004	0.002	0.002	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
40	0.005	0.005	0.005	0.002	0.002	0.002	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
45	0.006	0.006	0.006	0.003	0.003	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
50	0.008	0.007	0.007	0.003	0.003	0.003	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
60	0.011	0.010	0.010	0.005	0.004	0.004	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
70	0.014	0.014	0.013	0.006	0.006	0.005	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
80	0.019	0.017	0.016	0.008	0.007	0.007	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
90	0.023	0.022	0.020	0.010	0.009	0.009	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
100	0.028	0.026	0.025	0.012	0.011	0.010	0.003	0.003	0.003	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
120			0.035	0.017	0.016	0.015	0.004	0.004	0.004	0.001	0.001	0.001	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
140				0.022	0.021	0.019	0.006	0.005	0.005	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
160				0.028	0.026	0.025	0.007	0.007	0.006	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
180							0.009	0.008	0.008	0.003	0.003	0.003	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
200							0.011	0.010	0.010	0.004	0.003	0.003	0.002	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	
250							0.016	0.015	0.015	0.006	0.005	0.005	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	
300								0.021	0.021	0.008	0.007	0.007	0.003	0.003	0.003	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	
350									0.010	0.010	0.009	0.004	0.004	0.004	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	
400									0.013	0.012	0.012	0.006	0.005	0.005	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	0.000	
450									0.017	0.015	0.015	0.007	0.006	0.006	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	
500										0.008	0.008	0.008	0.002	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	
550										0.010	0.009	0.009	0.003	0.002	0.002	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	
600										0.012	0.011	0.011	0.003	0.003	0.003	0.001	0.001	0.001	0.000	0.000	0.000	0.000	0.000	
650											0.013	0.012	0.004	0.003	0.003	0.001	0.001	0.001	0.001	0.000	0.000	0.000	0.000	
700													0.004	0.004	0.004	0.001	0.001	0.001	0.001	0.000	0.000	0.000	0.000	
760															0.005	0.004	0.004	0.002	0.001	0.001	0.001	0.001	0.001	
1000															0.008	0.007	0.007	0.003	0.002	0.002	0.001	0.001	0.001	
2000																					0.004	0.004	0.004	

NOTES:

4. Table 6 is based on the Hazen-Williams formula:

$$P = \frac{4.52Q^{1.85}}{C^{1.85} d^{4.87}}$$

Where:

P= friction loss, psi per linear foot

Q= flow, g.p.m.

d= average I.D., in inches

C= constant, 150

TABLE 7. Pressure Loss in Fittings and Valves Expressed as Equivalent Length of Tube, feet

Nominal or Standard Size, in	Fittings					Valves			
	Standard Ell		90° Tee		Coupling	Ball	Gate	Btfly	Check
	90°	45°	Side Branch	Straight Run					
3/8	.5	—	1.5	—	—	—	—	—	1.5
1/2	1	.5	2	—	—	—	—	—	2
5/8	1.5	.5	2	—	—	—	—	—	2.5
3/4	2	.5	3	—	—	—	—	—	3
1	2.5	1	4.5	—	—	.5	—	—	4.5
1 1/4	3	1	5.5	.5	.5	.5	—	—	5.5
1 1/2	4	1.5	7	.5	.5	.5	—	—	6.5
2	5.5	2	9	.5	.5	.5	.5	7.5	9
2 1/2	7	2.5	12	.5	.5	—	1	10	11.5
3	9	3.5	15	1	1	—	1.5	15.5	14.5
3 1/2	9	3.5	14	1	1	—	2	—	12.5
4	12.5	5	21	1	1	—	2	16	18.5
5	16	6	27	1.5	1.5	—	3	11.5	23.5
6	19	7	34	2	2	—	3.5	13.5	26.5
8	29	11	50	3	3	—	5	12.5	39

NOTES: Allowances are for streamlined soldered fittings and recessed threaded fittings.
 For threaded fittings, double the allowances shown in the table.
 The equivalent lengths presented above are based upon a C factor of 150 in the Hazen-Williams friction loss formula. The lengths shown are rounded to the nearest half foot.

FIGURE 2. Collapse Pressure of Copper Tube, Types K, L and M




FIGURE 3. Expansion vs. Temperature Change for Copper Tube




TABLE 8. Radii of Coiled Expansion Loops and Developed Lengths of Expansion Offsets
(See Figure 5)

Expected Expansion, inches	Radius "R", inches, for Nominal or Standard Tube Sizes Shown Length "L", inches, for Nominal or Standard Tube Sizes Shown													
	1/4	3/8	1/2	3/4	1	1 1/4	1 1/2	2	2 1/2	3	3 1/2	4	5	
1/2	R	6	7	8	9	11	12	13	15	16	18	19	20	23
	L	38	44	50	59	67	74	80	91	102	111	120	128	142
1	R	9	10	11	13	15	17	18	21	23	25	27	29	32
	L	54	63	70	83	94	104	113	129	144	157	169	180	201
1 1/2	R	11	12	14	16	18	20	22	25	28	30	33	35	39
	L	66	77	86	101	115	127	138	158	176	191	206	220	245
2	R	12	14	16	19	21	23	25	29	32	35	38	41	45
	L	77	89	99	117	133	147	160	183	203	222	239	255	284
2 1/2	R	14	16	18	21	24	26	29	33	36	40	43	45	51
	L	86	99	111	131	149	165	179	205	227	248	267	285	318
3	R	15	17	19	23	26	29	31	36	40	43	47	50	55
	L	94	109	122	143	163	180	196	224	249	272	293	312	348
3 1/2	R	16	19	21	25	28	31	34	39	43	47	50	54	60
	L	102	117	131	155	176	195	212	242	269	293	316	337	376
4	R	17	20	22	26	30	33	36	41	46	50	54	57	64
	L	109	126	140	166	188	208	226	259	288	314	338	361	402

FIGURE 4 a, b, c. Coiled Expansion Loops and Offsets






FIGURE 5. Selected Pressure Fittings


ADAPTERS




FTG x M
Adapter




FTG x F
Adapter




C x C
Union



C x M
Adapter




C x F
Adapter




C x C x F
Tee


ELBOWS




C x C
45° Elbow




C x C
90° Elbow




C x C x C
Tee



FTG x C
45° Elbow




FTG x C
90° Elbow




C x FTG x C
Tee


COUPLINGS




C x C
Roll Stop



C x C
Staked Stop




C x C
No Stop



C x C
Reducing

GENERAL NOTES: (a) Fittings are designated by size in the order: 1x2x3 (b) Fitting designs and drawings are for illustration only.

FIGURE 6. Dimensions of Solder Joint Fitting Ends




Drawings and designs of fittings are for illustration only.

TABLE 9. Dimensions of Solder Joint Ends for Wrought (W) and Cast (C) Pressure Fittings, inches

Nominal or Standard Fittings Size, In.	Type	Male End			Female End			For use with tube size			
		Outside Diameter A		Length K	Inside Diameter F		Depth G	under ASTM B 88	under ASTM B 280	under ASTM B 819	under ASTM B 837
		Min.	Max.	Min.	Min.	Max.	Min.				
1/8	W	.248	.251	.38	.252	.256	.31	*	1/4	*	1/4
1/4	C W	.373	.376	.38	.377	.381	.31	1/4	3/8	1/4	3/8
3/8	C W	.497	.501	.44	.502	.506	.38	3/8	1/2	3/8	1/2
1/2	C W	.622	.626	.56	.627	.631	.50	1/2	5/8	1/2	5/8
5/8	W	.747	.751	.81	.752	.756	.75	5/8	3/4	5/8	3/4
3/4	C W	.872	.876	.81	.877	.881	.75	3/4	7/8	3/4	7/8
1	C W	1.122	1.127	.97	1.128	1.132	.91	1	1 1/8	1	1 1/8
1 1/4	C W	1.372	1.377	1.03	1.378	1.382	.97	1 1/4	1 3/8	1 1/4	*
1 1/2	C W	1.621	1.627	1.16	1.628	1.633	1.09	1 1/2	1 5/8	1 1/2	*
2	C W	2.121	2.127	1.41	2.128	2.133	1.34	2	2 1/8	2	*
2 1/2	C W	2.621	2.627	1.53	2.628	2.633	1.47	2 1/2	2 5/8	2 1/2	*
3	C W	3.121	3.127	1.72	3.128	3.133	1.66	3	3 1/8	3	*
3 1/2	C W	3.621	3.627	1.97	3.628	3.633	1.91	3 1/2	3 5/8	3 1/2	*
4	C W	4.121	4.127	2.22	4.128	4.133	2.16	4	4 1/8	4	*
5	C W	5.121	5.127	2.72	5.128	5.133	2.66	5	*	5	*
6	C W	6.121	6.127	3.22	6.128	6.133	3.09	6	*	6	*
8	C W	8.119	8.127	4.09	8.128	8.133	3.97	8	*	8	*
10	C	10.119	10.127	4.12	10.128	10.133	4.00	10	*	*	*
12	C	12.119	12.127	4.62	12.128	12.133	4.50	12	*	*	*

* Copper tube under this standard is not commercially available.

FIGURE 7. Melting Temperature Ranges for Copper and Copper Alloys, Brazing Filler Metals, Brazing Flux and Solders



NOTE: * Melting ranges of solder alloys are in accordance with the alloy manufacturers' product information and may not match the melting ranges shown in ASTM B32.

TABLE 10. Solder Requirements for Solder Joint Pressure Fittings, length in inches¹

Nominal or Standard Size, inches	O.D. of Tube, inches	Cup Depth of Fitting, inches	Joint Clearance, inches										Wt. in lbs at .010 clearance per 100 joints
			0.001	0.002	0.003	0.004	0.005	0.006	0.007	0.008	0.009	0.010	
1/4	.375	.310	.030	.060	.089	.119	.149	.179	.208	.238	.268	.298	.097
3/8	.500	.380	.049	.097	.146	.195	.243	.292	.341	.389	.438	.486	.159
1/2	.625	.500	.080	.160	.240	.320	.400	.480	.560	.640	.720	.800	.261
5/8	.750	.620	.119	.238	.357	.476	.595	.714	.833	.952	1.072	1.191	.389
3/4	.875	.750	.168	.336	.504	.672	.840	1.008	1.176	1.344	1.512	1.680	.548
1	1.125	.910	.262	.524	.786	1.048	1.311	1.573	1.835	2.097	2.359	2.621	.856
1 1/4	1.375	.970	.341	.683	1.024	1.366	1.707	2.049	2.390	2.732	3.073	3.415	1.115
1 1/2	1.625	1.090	.454	.907	1.361	1.814	2.268	2.721	3.175	3.628	4.082	4.535	1.480
2	2.125	1.340	.729	1.458	2.187	2.916	3.645	4.374	5.103	5.833	6.562	7.291	2.380
2 1/2	2.625	1.470	.988	1.976	2.964	3.952	4.940	5.928	6.916	7.904	8.892	9.880	3.225
3	3.125	1.660	1.328	2.656	3.985	5.313	6.641	7.969	9.297	10.626	11.954	13.282	4.335
3 1/2	3.625	1.910	1.773	3.546	5.318	7.091	8.864	10.637	12.409	14.182	15.955	17.728	5.786
4	4.125	2.160	2.281	4.563	6.844	9.125	11.407	13.688	15.969	18.250	20.532	22.813	7.446
5	5.125	2.660	3.490	6.981	10.471	13.962	17.452	20.943	24.433	27.924	31.414	34.905	11.392
6	6.125	3.090	4.846	9.692	14.538	19.383	24.229	29.075	33.921	38.767	43.613	48.459	15.815
8	8.125	3.970	8.259	16.518	24.777	33.035	41.294	49.553	57.812	66.071	74.330	82.589	26.955
10	10.125	4.000	10.370	20.739	31.109	41.478	51.848	62.218	72.587	82.957	93.326	103.696	33.845
12	12.125	4.500	13.970	27.940	41.910	55.881	69.851	83.821	97.791	111.761	125.731	139.701	45.596

¹ Using 1/8-inch diameter (No. 9) Wire Solder (1 inch length = .01227 cubic inches).

² Actual consumption depends on workmanship.


³ Includes an allowance of 100% to cover wastage and loss.

NOTE: Flux requirements are usually 2 oz per lb of solder.

Average Actual Consumption²

For Estimating Purposes³

FIGURE 8. Brazing Flux Recommendations



Triangles, denoting when to use flux, are surrounded by tube type, fitting type and brazing filler type.

NOTE: When joining copper tube to a wrought fitting using BCuP filler, **no** flux is required.

TABLE 11. Typical Brazing Filler Metal Consumption

Tube Nominal or Standard Size, inches	Filler Metal Length, inches				Average Weight per 100 Joints, pounds ¹
	1/16-inch Wire	1/8-in x .050-in Rod	3/32-inch Wire	1/8-inch Wire	
1/4	1/2	1/4	1/4	1/8	.04
3/8	5/8	3/8	3/8	1/4	.06
1/2	1 1/8	5/8	1/2	3/8	.10
5/8	1 5/8	7/8	5/8	1/2	.15
3/4	2 1/4	1 1/8	1	5/8	.21
1	3 1/2	1 3/4	1 5/8	7/8	.32
1 1/4	4 1/2	2 1/4	2	1 1/4	.42
1 1/2	—	3	2 5/8	1 1/2	.56
2	—	4 3/4	4 3/8	2 1/2	.90
2 1/2	—	6 1/2	5 7/8	3 3/8	1.22
3	—	8 5/8	7 7/8	4 1/2	1.64
3 1/2	—	11 1/2	10 1/2	5 7/8	2.18
4	—	14 7/8	13 1/2	7 5/8	2.81
5	—	22 5/8	20 1/2	11 5/8	4.30
6	—	31 1/2	28 1/2	16	5.97
8	—	53 1/2	48 1/2	27 3/8	10.20
10	—	67 1/4	61	34 1/4	12.77
12	—	90 1/2	82	46 1/8	17.20

¹ The amount of filler metal indicated is based on an average two-thirds penetration of the cup and with no provision for a fillet. For estimating purposes, actual consumption may be two to three times the amounts indicated in this table, depending on the size of joints, method of application and level of workmanship.

NOTE: 1090 inches of 1/16-inch wire = 1 pound
 534 inches of 1/8-inch x .050-inch rod = 1 pound
 484 inches of 3/32-inch wire = 1 pound
 268 inches of 1/8-inch wire = 1 pound

TABLE 12. Filler Metals for Brazing

AWS Classification ¹	Principal Elements, percent						Temperature F	
	Silver(Ag)	Phosphorus(P)	Zinc(Zn)	Cadmium(Cd)	Tin(Sn)	Copper(Cu)	Solidus	Liquidus
BCup-2	—	7.00-7.5	—	—	—	Remainder	1310	1460
BCup-3	4.8-5.2	5.8-6.2	—	—	—	Remainder	1190	1495
BCup-4	5.8-6.2	7.0-7.5	—	—	—	Remainder	1190	1325
BCup-5	14.5-15.5	4.8-5.2	—	—	—	Remainder	1190	1475
BAG-1 ²	44-46	—	14-18	23-25 ²	—	14-16	1125	1145
BAG-2 ²	34-36	—	19-23	17-19 ²	—	25-27	1125	1295
BAG-5	44-46	—	23-27	—	—	29-31	1225	1370
BAG-7	55-57	—	15-19	—	4.5-5.5	21-23	1145	1205

¹ ANSI/AWS A5.8 Specification for Filler Metals for Brazing

² **WARNING:** BAG-1 and BAG-2 contain cadmium. Heating when brazing can produce highly toxic fumes. Avoid breathing fumes. Use adequate ventilation. Refer to ANSI/ASC Z49 1 Safety in Welding and Cutting.

WORKING WITH COPPER TUBE



IV. BENDING

Because of its exceptional formability, copper can be formed as desired at the job site. Copper tube, properly bent, will not collapse on the outside of the bend and will not buckle on the inside of the bend. Tests demonstrate that the bursting strength of a bent copper tube can actually be greater than it was before bending.

Because copper is readily formed, expansion loops and other bends necessary in an assembly are quickly and simply made if the proper method and equipment are used. Simple hand tools employing mandrels, dies, forms and fillers, or power-operated bending machines can be used.

Both annealed tube and hard drawn tube can be bent with the appropriate hand benders. The proper size of bender for each size tube must be used. For a guide to typical bend radii, see **Table 13**.

The procedure for bending copper tube with a lever-type hand bender is illustrated in **Figure 9**.

TABLE 13: Bending Guide for Copper Tube

TABLE 13. Bending Guide for Copper Tube

Nominal, Standard Size, in	Tube Type	Temper	Minimum Bend Radius ¹ , in
1/4	K, L	Annealed	3/4
3/8	K, L	Annealed	1 1/2
	K, L, M	Drawn	1 3/4
1/2	K, L	Annealed	2 1/4
	K, L, M	Drawn	2 1/2
3/4	K, L	Annealed	3
	K, L	Drawn	3
1	K, L	Annealed	4
1 1/4	K, L	Annealed	9

¹ The radii stated are the minimums for mechanical bending equipment only.

(A) With the handles at 180°F and the tube-holding clip raised out of the way, insert the tube in the forming-wheel groove.


(B) Place the tube-holding clip over the tube and bring the handle into an approximately right angle position, engaging the forming shoe over the tube. The zero mark on the forming wheel should then be even with the front edge of the forming shoe.

(C) Bend by pulling the handles toward each other in a smooth,


continuous motion. The desired angle of the bend will be indicated by the calibrations on the forming wheel.

(D) Remove the bent tube by pivoting the handle to a right angle with the tube, disengaging the forming shoe. Then release the tube-holding clip.


The tool illustrated is just one of many available to the industry. Of course, if the manufacturer of the tube bender has special instructions regarding his product, such instructions should be followed.



A



B



C



D

FIGURE 9: Bending Using a Lever-Type Hand Bender (tool shown is appropriate for use with annealed tube only)

V. JOINING

Soldered joints, with capillary fittings, are used in plumbing for water lines and for sanitary drainage. Brazed joints, with capillary fittings, are used where greater joint strength is required or where service temperatures are as high as 350°F. Brazing is preferred, and often required, for joints in refrigeration piping.

Mechanical joints are used frequently for underground tubing, for joints where the use of heat is impractical and for joints that may have to be disconnected from time to time. Copper tube may also be joined by butt-welding without the use of fittings. Care must be taken to use proper welding procedures.

Fittings

Fittings for copper water tube used in plumbing and heating are made to the following standards: *Cast Copper Alloy Threaded Fittings* (ASME B16.15); *Cast Copper Alloy Solder Joint Pressure Fittings* (ASME B16.18); *Wrought Copper and Copper Alloy Solder Joint Pressure Fittings* (ASME B16.22); *Wrought Copper LW Solder Joint Pressure Fittings (MSS SP104)*; *Welded Fabricated Copper Solder Joint Pressure Fittings (MSS SP109)*; *Cast Copper Alloy Solder Joint Drainage Fittings DWV* (ASME B16.23); *Bronze Pipe Flanges and Flanged Fittings* (ASME B16.24); *Cast Copper Alloy Fittings for Flared Copper Tubes* (ASME B16.26); *Wrought Copper and Wrought Copper-Alloy Solder Joint Drainage Fittings DWV* (ASME B16.29), and *Wrought Copper and*

Copper Alloy Braze-Joint Pressure Fittings (ASME B16.50). Examples of solder joint end dimensions are shown in **Figure 6**, page 37.

Cast alloy pressure fittings are available in all standard tube sizes and in a limited variety of types to cover needs for plumbing and mechanical systems. They can be either soldered or brazed, although brazing cast fittings requires care. Wrought copper pressure fittings are available over a wide range of sizes and types. These, too, can be joined by either soldering or brazing; wrought fittings are preferred where brazing is the joining method. Otherwise, the choice between cast and wrought fittings is largely a matter of the user's preference and availability.

Flared-tube fittings provide metal-to-metal contact similar to ground joint unions; both can be easily taken apart and reassembled. They are especially useful where residual water cannot be removed from the tube and soldering is difficult. Flared joints may be required where a fire hazard exists and the use of a torch to make soldered or brazed joints is not allowed. Also, soldering under wet conditions can be very difficult; flared joints are preferred under such circumstances.

Solders

Soldered joints depend on capillary action drawing free-flowing molten solder into the gap between the fitting and the tube. Flux acts as a cleaning and wetting agent and, when properly applied, permits uniform spreading of the molten solder over the surfaces to be joined.

The selection of a solder depends primarily on the operating pressure and temperature of the system. Consideration should also be given to the stresses on joints caused by thermal expansion and contraction. However, stresses due to temperature changes should not be significant in two commonly encountered cases: when tube lengths are short, or when expansion loops are used in long tube runs.

Rated internal working pressures for solder joints made with copper tube using 50-50 tin-lead solder (ASTM B 32 Alloy Sn50), 95-5 tin-antimony solder (ASTM B 32 Alloy Sb5), and several lead-free solders (ASTM B 32 Alloy E and Alloy HB) are listed in **Table 4**, page 28.

The 50-50 tin-lead solder is suitable for moderate pressures and temperatures. For higher pressures, or where greater joint strength is required, 95-5 tin-antimony solder and alloys E and HB can be used. For continuous operation at temperatures exceeding 250°F, or where the highest joint strength is required, brazing filler metals should be used.

Most solders referenced in ASTM B 32, *Standard Specification for Solder Metal*, can be used to join copper tube and fittings in potable water systems. **Solders containing lead at concentrations of greater than 0.2% are banned for potable water systems by the 1986 amendment to the Federal Safe Drinking Water Act.** The 50-50 tin-lead solders may be used in some HVAC, drainage and other piping systems in some jurisdictions.

Solder is generally used in wire form, but solder-flux pastes are also available. These are finely granulated solders in suspension in a paste flux. When using a solder-flux paste, adding additional wire solder to the joint is required. Use the same type solder (*e.g.*, 50-50 or 95-5) as that used in the paste.

Fluxes

The functions of soldering flux are to remove residual traces of oxides, to promote wetting and to protect the surfaces to be soldered from oxidation

during heating. The flux should be applied to clean surfaces and only enough should be used to lightly coat the areas to be joined.

An oxide film may re-form quickly on copper after it has been cleaned. Therefore, the flux should be applied as soon as possible after cleaning.

The fluxes best suited for soldering copper and copper alloy tube should meet the requirements of ASTM B 813, *Standard Specification for Liquid and Paste Fluxes for Soldering*

Applications of Copper and Copper Alloy Tube (see page 44).

Some fluxes identified by their manufacturers as "self-cleaning" present a risk in their use. There is no doubt that a strong, corrosive flux can remove some oxides and dirt films. However, when highly corrosive fluxes are used this way, there is always uncertainty whether uniform cleaning has been achieved and whether corrosive action from flux residue continues after the soldering has been completed.

VI. SOLDERED JOINTS

The American Welding Society defines soldering as “a group of joining processes that produce coalescence of materials by heating them to a soldering temperature and by using a filler metal (solder) having a liquidus not exceeding 840°F and below the solidus of the base metals.” In actual practice, most soldering is done at temperatures from about 350°F to 600°F.

To consistently make satisfactory joints, the following sequence of joint preparation and operations, based on ASTM Standard Practice B 828, should be followed:

- measuring and cutting
- reaming
- cleaning
- fluxing
- assembly and support
- heating
- applying the solder
- cooling and cleaning

The techniques described produce leak-tight soldered joints between copper and copper alloy tube and fittings, either in shop operations or in the field. Skill and knowledge are required to produce a satisfactorily soldered joint.

Measuring and Cutting

Accurately measure the length of each tube segment (**Figure 10**). Inaccuracy can compromise joint quality. If the tube is too short, it will not reach all the way into the cup of the fitting and a proper joint cannot be made. If the tube segment is too long, system strain may be introduced which could affect service life.

Cut the tube to the measured lengths. Cutting can be accomplished in a number of different ways to produce a satisfactory squared end. The tube can be cut with a disc-type tube cutter (**Figure 11**), a hacksaw, an abrasive wheel, or with a stationary or portable bandsaw. Care must be taken that the tube is not deformed while being cut. Regardless of method, the cut must be square to the run of the tube so that the tube will seat properly in the fitting cup.




FIGURE 10: Measuring




FIGURE 11: Cutting

Reaming

Ream all cut tube ends to the full inside diameter of the tube to remove the small burr created by the cutting operation. If this rough, inside edge is not removed by reaming, erosion-corrosion may occur due to local turbulence and increased local flow velocity in the tube. A properly reamed piece of tube provides a smooth surface for better flow.

Remove any burrs on the outside of the tube ends, created by the cutting operation, to ensure proper entrance of the tube into the fitting cup.

Tools used to ream tube ends include the reaming blade on the tube cutter, half-round or round files (**Figure 12**), a pocket knife (**Figure 13**), and a suitable deburring tool (**Figure 14**). With soft tube, care must be taken not to deform the tube end by applying too much pressure.

Soft temper tube, if deformed, can be brought back to roundness with a sizing tool. This tool consists of a plug and sizing ring.




FIGURE 12: Reaming: File




FIGURE 13: Reaming: Pocket Knife




FIGURE 14: Reaming: Deburring Tool

Cleaning

The removal of all oxides and surface soil from the tube ends and fitting cups is crucial to proper flow of solder metal into the joint. Failure to remove them can interfere with capillary action and may lessen the strength of the joint and cause failure.

Lightly abrade (clean) the tube ends using sand cloth (Figure 15) or nylon abrasive pads (Figure 16) for a distance slightly more than the depth of the fitting cups.

Clean the fitting cups by using abrasive cloth, abrasive pads or a properly sized fitting brush (Figure 17).

The capillary space between tube and fitting is approximately 0.004 in. Solder metal fills this gap by capillary action. This spacing is critical for the solder metal to flow into the gap and form a strong joint.

Copper is a relatively soft metal. If too much material is removed from

the tube end or fitting cup, a loose fit may result in a poor joint.

Chemical cleaning may be used if the tube ends and fittings are thoroughly rinsed after cleaning according to the procedure furnished by the cleaner manufacturer. Do not touch the cleaned surface with bare hands or oily gloves. Skin oils, lubricating oils and grease impair the soldering operation.




FIGURE 15: Cleaning: Sand Cloth



FIGURE 16: Cleaning: Abrasive Pad



FIGURE 17: Cleaning: Fitting Brush

Applying Flux

Use a flux that will dissolve and remove traces of oxide from the cleaned surfaces to be joined, protect the cleaned surfaces from reoxidation during heating, and promote wetting of the surfaces by the solder metal, as recommended in the general requirements of ASTM B 813. Apply a thin even coating of flux with a brush to both tube and fitting as soon as possible after cleaning (Figures 18 and 19).

WARNING: Do not apply with fingers. Chemicals in the flux can be harmful if carried to the eyes, mouth or open cuts.

Use care in applying flux. Careless workmanship can cause problems long after the system has been installed. If excessive amounts of flux are used, the flux residue can cause corrosion. In extreme cases, such flux corrosion could perforate the wall of the tube, fitting or both.




FIGURE 18: Fluxing: Tube




FIGURE 19: Fluxing: Fitting

Assembly and Support

Insert the tube end into fitting cup, making sure that the tube is seated against the base of the fitting cup (Figure 20). A slight twisting motion ensures even coverage by the flux. Remove excess flux from the exterior of the joint with a cotton rag (Figure 21).

Support the tube and fitting assembly to ensure a uniform capillary space around the entire circumference of the joint. Uniformity of capillary space will ensure good capillary flow (Figure 27, page 48), of the molten-solder metal. Excessive joint clearance can lead to solder metal cracking under conditions of stress or vibration.

The joint is now ready for soldering. Joints prepared and ready for soldering must be completed the same day and not left unfinished overnight.



FIGURE 20: Assembly



FIGURE 21: Removing Excess Flux

Heating

WARNING: When dealing with an open flame, high temperatures and flammable gases, safety precautions must be observed as described in ANSI/ASC Z49.1.

Begin heating with the flame perpendicular to the tube (Figure 27, position 1 and Figure 22). The copper tube conducts the initial heat into the fitting cup for even distribution of heat in the joint area. The extent of this preheating depends upon the size of the joint. Preheating of the assembly should include the entire circumference of the tube in order to bring the entire assembly up to a suitable preheat condition. However, for joints in the horizontal position, avoid directly preheating the top of the joint to avoid burning the soldering flux. The natural tendency for heat to rise will ensure adequate preheat of the top of the assembly. Experience will indicate the amount of heat and the time needed.

Next, move the flame onto the fitting cup (Figure 27, position 2 and Figure 23). Sweep the flame alternately between the fitting cup and the tube a distance equal to the depth of the fitting cup (Figure 27, position 3). Again, preheating the circumference of the assembly as described above, with the torch at the base of the fitting cup (Figure 27, position 4), touch the solder to the joint. If the solder does not melt, remove it and continue heating.

CAUTION: Do not overheat the joint or direct the flame into the face of the fitting cup. Overheating could burn the flux, which will




FIGURE 22: Pre-Heating Tube




FIGURE 23: Pre-Heating Fitting

destroy its effectiveness and the solder will not enter the joint properly.

When the solder melts, apply heat to the base of the cup to aid capillary action in drawing the molten solder into the cup towards the heat source.

The heat is generally applied using an air-fuel torch. Such torches use acetylene or an LP gas. Electric resistance soldering tools can also be used (Figure 24, page 48). They employ heating electrodes and should be considered when an open flame is a concern.

Applying Solder

For joints in the horizontal position, start applying the solder metal slightly off-center at the bottom of the joint (Figure 27, position a, and Figure 25). When the solder begins to melt from the heat of the tube and fitting, push the solder straight into the joint while keeping the torch at




FIGURE 24: Electric Resistance Hand Tool

the base of the fitting and slightly ahead of the point of application of the solder. Continue this technique across the bottom of the fitting and up one side to the top of the fitting (**Figure 27**, position b).

The now-solidified solder at the bottom of the joint has created an effective dam that will prevent the solder from running out of the joint as the side and top of the joint are being filled.

Return to the point of beginning, overlapping slightly (**Figure 27**, position c), and proceed up the uncompleted side to the top, again, overlapping slightly (**Figure 27**, position d). While soldering, small drops may appear behind the point of solder application, indicating the joint is full to that point and will take no more solder. Throughout this process you are using all three physical states of the solder: solid, pasty and liquid.

For joints in the vertical position, make a similar sequence of overlapping passes starting wherever is convenient.

Solder joints depend on capillary action drawing free-flowing molten solder into the narrow clearance between the fitting and the tube. Molten solder metal is drawn into the joint by capillary action regardless of whether the solder flow is upward, downward or horizontal.

Capillary action is most effective when the space between surfaces to be joined is between 0.002 inch and 0.005 inch. A certain amount of looseness of fit can be tolerated, but too loose a fit can cause difficulties with larger size fittings.

For joining copper tube to solder-cup valves, follow the manufacturer's




FIGURE 25: Soldering



FIGURE 26: Cleaning




FIGURE 27: Schematic of Solder Joint

instructions. The valve should be in a partially open position before applying heat, and the heat should be applied primarily to the tube. Commercially available heat-sink materials can also be used for protection of temperature-sensitive components during the joining operation.

The amount of solder consumed when adequately filling the capillary space between the tube and either wrought or cast fittings may be estimated from **Table 10**, page 39. The flux requirement is usually 2 ounces per pound of solder.

Cooling and Cleaning

Allow the completed joint to cool naturally. Shock cooling with water may stress the joint. When cool, clean off any

remaining flux residue with a wet rag (**Figure 26**). Whenever possible, based on end use, completed systems should be flushed to remove excess flux and debris.

Testing

Test all completed assemblies for joint integrity. Follow the testing procedure prescribed by applicable codes governing the intended service.

VII. BRAZED JOINTS

Strong, leak-tight brazed connections for copper tube may be made by brazing with filler metals which melt at temperatures in the range between 1100°F and 1500°F, as listed in **Table 12**, page 40. Brazing filler metals are sometimes referred to as “hard solders” or “silver solders.” **These confusing terms should be avoided.**

The temperature at which a filler metal starts to melt on heating is the *solidus* temperature; the *liquidus* temperature is the higher temperature at which the filler metal is completely melted. The *liquidus* temperature is the minimum temperature at which brazing will take place.

The difference between *solidus* and *liquidus* is the *melting range* and may be of importance when selecting a filler metal. It indicates the width of the working range for the filler metal and the speed with which the filler metal will become fully solid after brazing. Filler metals with narrow ranges, with or without silver, solidify more quickly and, therefore, require careful application of heat. The melting ranges of common brazing metals are shown in **Figure 8a**.

Brazing Filler Metals

Brazing filler metals suitable for joining copper tube are of two classes: (1) the BCuP series alloys containing phosphorus and (2) the BAg series alloys containing a high silver content.

The two classes differ in their melting, fluxing and flowing characteristics and this should be considered in selection of a filler metal. (See **Table 12**.) While any of the listed filler metals may be used, those most commonly

used in plumbing, HVAC refrigeration and fire sprinkler systems are BCuP-2 (for closer tolerances), BCuP-3, 4 or 5 (where close tolerances cannot be held) and BAg-1, BAg-5 and BAg-7. The BCuP series filler metals are more economical than the BAg series, and are better suited for general piping applications. BAg series filler metals should be used when joining dissimilar metals, or the specific characteristics of the BAg series filler metals are required. For joining copper tube, any of these filler metals will provide the necessary strength when used with standard solder-type fittings or commercially available short-cup brazing fittings.

According to the American Welding Society (AWS), the strength of the brazed joint will meet or exceed that of the tube and fitting being joined when the joint overlap and the depth of the filler metal penetration is a minimum of three times the thickness of the thinner base metal (tube or fitting), and a well-developed fillet is present.

The strength of a brazed copper tube joint does not vary much with the different filler metals but depends mainly on maintaining the proper clearance between the outside of the tube and the cup of the fitting. Copper tube and solder-type fittings are accurately made for each other, and the tolerances permitted for each assure the capillary space will be within the limits necessary for a joint of satisfactory strength.

The rated internal working pressures of brazed copper tube systems at service temperatures up to

350°F (the temperature of saturated steam at 120 psi) are shown in **Table 4**, page 28. These pressure ratings should be used only when the correct capillary space has been maintained.

Fluxes

The fluxes used for brazing copper joints are different in composition from soldering fluxes. The two types cannot be used interchangeably.

Unlike soldering fluxes, brazing fluxes are water based. Similar to soldering fluxes, brazing fluxes dissolve and remove residual oxides from the metal surface, protect the metal from reoxidation during heating and promote wetting of the surfaces to be joined by the brazing filler metal.

Brazing fluxes also provide the craftsman with an indication of temperature (**Figure 7b**). If the outside of the fitting and the heat-affected area of the tube are covered with flux (in addition to the end of the tube and the cup), oxidation will be minimized and the appearance of the joint will be greatly improved.

The fluxes best suited for brazing copper and copper alloy tube should meet AWS Standard A5.31, Type FB3-A or FB3-C.

Figure 8, page 39, illustrates the need for brazing flux with different types of copper and copper-alloy tube, fittings and filler metals when brazing.

Assembly

Assemble the joint by inserting the tube into the socket hard against the stop and turn if possible. The assembly should be firmly supported so that it

will remain in alignment during the brazing operation.

Applying Heat and Brazing

Apply heat to the parts to be joined, preferably with an oxy-fuel torch with a neutral flame. Air-fuel is sometimes used on smaller sizes. Heat the tube first, beginning about one inch from the edge of the fitting, sweeping the flame around the tube in short strokes at right angles to the axis of the tube (**Figure 27**, position 1).

It is very important that the flame be in motion and not remain on any one point long enough to damage the tube. The flux may be used as a guide as to how long to heat the tube. The behavior of flux during the brazing cycle is described in **Figure 7**.

Switch the flame to the fitting at the base of the cup (**Figure 27**, position 2). Heat uniformly, sweeping the flame from the fitting to the tube until the flux on the fitting becomes quiet. Avoid excessive heating of cast fittings, due to the possibility of cracking.

When the flux appears liquid and transparent, start sweeping the flame back and forth along the axis of the joint to maintain heat on the parts to be joined, especially toward the base of the cup of the fitting (**Figure 27**, position 3). The flame must be kept moving to avoid melting the tube or fitting.

For 1-inch tube and larger, it may be difficult to bring the whole joint up to temperature at one time. It frequently will be found desirable to use an oxy-fuel, multiple-orifice heating tip to maintain a more uniform temperature over large areas. A mild preheating of the entire fitting is recommended for larger sizes, and the use of a second torch to retain a uniform preheating of the entire fitting assembly may be necessary in larger diameters. Heating can then proceed as outlined in the steps above.

Apply the brazing filler metal at a point where the tube enters the socket of the fitting. When the proper temperature is reached, the filler metal will flow readily into the space between the tube and fitting socket, drawn in by the natural force of capillary action.

Keep the flame away from the filler metal itself as it is fed into the joint. The temperature of the tube and fitting at the joint should be high enough to melt the filler metal.

Keep both the fitting and tube heated by moving the flame back and forth from one to the other as the filler metal is drawn into the joint.

When the joint is properly made, filler metal will be drawn into the fitting socket by capillary action, and a continuous fillet of filler metal will be visible completely around the joint. To aid in the development of this fillet during brazing, the flame should be kept slightly ahead of the point of filler metal application.

Horizontal and Vertical Joints

When brazing horizontal joints, it is preferable to first apply the filler metal slightly off-center at the bottom of the joint, proceeding across the bottom of the joint and continuing up the side to the top of the joint. Then, return to the beginning point, overlapping slightly, and proceed up the uncompleted side to the top, again, overlapping slightly. This procedure is identical to that used for soldering.

Also, similar to the soldering process, make sure the operations overlap. On vertical joints it is immaterial where the start is made. If the opening of the socket is pointing down, care should be taken to avoid overheating the tube, as this may cause the brazing filler metal to run down the outside of the tube.

Removing Residue

After the brazed joint has cooled the flux residue should be removed with a clean cloth, brush or swab using warm water. Remove all flux residue to avoid the risk of the hardened flux temporarily retaining pressure and masking an imperfectly brazed joint. Wrought fittings may be cooled more readily than cast fittings, but all fittings should be allowed to cool naturally before wetting.

General Hints and Suggestions

If the filler metal fails to flow or has a tendency to ball up, it indicates oxidation on the metal surfaces or insufficient heat on the parts to be joined. If tube or fitting start to oxidize during heating there is too little flux. If the filler metal does not enter the joint and tends to flow over the outside of either member of the joint, it indicates that one member is overheated or the other is underheated.

Testing

Test all completed assemblies for joint integrity. Follow the testing procedure prescribed by applicable codes governing the intended service.

Purging

Some installations, such as medical gas, high-purity gas and ACR systems, require the use of an inert gas during the brazing process. The purge gas displaces oxygen from the interior of the system while it is being subjected to the high temperatures of brazing and therefore eliminates the possibility of oxide formation on the interior tube surface.

Purge gas flow rates and methods of application should be included in the Brazing Procedure Specifications of these applications.

VIII. FLARED JOINTS

While copper tube is usually joined by soldering or brazing, there are times when a mechanical joint may be required or preferred. Flared fittings (Figures 28 and 29) are an alternative



FIGURE 28: Flare Fitting/Flared Joint During Assembly



FIGURE 29: Completed Flared Joint

when the use of an open flame is either not desired or impractical. Water service applications generally use a flare to iron pipe connection when connecting the copper tube to the main and/or the meter. In addition, copper

tube used for Fuel Gas (Liquefied Petroleum (LP), Propane Gas or Natural Gas may be joined utilizing flared brass fittings of single 45°-flare type, according to NFPA 54/ANSI. Z223.1 National Fuel Gas Code. All National Model Codes permit the use of flare joints, but it is important to check with the authority having jurisdiction (AHJ) to determine acceptance for a specific application in any particular jurisdiction.

A flare joint should be made with an appropriate tool such as those supplied by a number of tubing/piping tool manufacturers. Make sure to use a tool that matches the outside diameter of the tube being flared and that has the appropriate flare angle, commonly 45° (the physical characteristics of which should be in accordance with the *Society of Automotive Engineers* SAE J533 Standard – Flares for Tubing). The tool usually consists of flaring bars with openings for various tube sizes and a yoke that contains the flaring cone and a clamp to grip the flaring bars.

When flaring Types L or Type K copper tube, annealed or soft temper tube should be used. It is possible to flare Types K, L or M rigid or hard temper tube, though prior to flaring it is usually necessary to anneal the end of the tube to be flared. The copper tube must be cut square using an appropriate tubing cutter. After cutting, the tube

must be reamed to the full inside diameter leaving no inside burr (Figure 30). Tube that is out of round prior to flaring should be resized back to round.



FIGURE 30: Reaming Prior to Flaring the Tube End

Failure to complete either of these steps can, lead to an inadequate seal of the flared joint and, ultimately, to joint failure. Dirt, debris and foreign substances should be removed from the tube end to be flared by mechanical cleaning. This can be accomplished with the use of an abrasive cloth (screen cloth, sand cloth, emery cloth or nylon abrasive cloth).

Now, place a flare nut over the end of the tube with the threads closest to the end being flared. Insert the tube between the flaring bars of the flaring tool in the appropriate opening for the diameter of the tube being flared. Adjust the height of the tube in the opening in accordance with the tool manufacturer's instructions, to achieve

sufficient length of the flare. Position the yoke with the flaring cone over the tube end and clamp the yoke in place. Turn the handle of the yoke clockwise (**Figure 31**). This lowers the flaring



FIGURE 31: Lowering the Flaring Cone into the Tube End

cone and forces the lip of the tube against the base of the flaring bar to create an angled flare that will mate securely with a corresponding flare-type fitting. Care should be taken not to over-tighten the cone and cause cracking or deformation of the tube and/or the tool. Some tools also provide a setting for *ironing* or burnishing the flare, as a final step to achieve a more consistent flare. The final flared tube end should have a smooth, even, round flare of sufficient length to fully engage the mating surface of the flare nut without protruding into the threads (**Figure 32**).

No material (*e.g.*, pipe joint compound) should be applied to the mating surfaces of the flare fitting and the flared tube end before attaching the flare nut to the fitting body.



FIGURE 32: Completed Flared Tube End

IX. ADDITIONAL JOINING METHODS

Soldering and brazing are fast and efficient methods of joining with standard torches and a variety of gases, facilitating high productivity on the job site.

There are also electric resistance soldering hand tools which employ heating electrodes for joining tube and fittings (**Figure 24**, page 48). The tools are lightweight and should be considered when an open flame is a concern.

Another joining technology involves a hand tool designed to

quickly pull tee connections and outlets from the run of the tube, thus reducing the number of tee fittings and brazed joints (**Figure 33**). It allows branches to be formed faster and usually results in a lower installed system cost.

A new mechanical joining system for copper tube offers a practical alternative to soldering and brazing large diameter tube. Grooved-end piping has been familiar to pipe fitters and sprinkler system contractors for many years. Since 1925, this

method of joining pipe has been used reliably on steel and iron pipe in HVAC, fire protection, process piping and related applications. Now this method of mechanical joining is available in a system for copper tube in sizes from 2 through 6 inches (**Figure 34**). Included are couplings, grooved copper 45- and 90-degree elbows, and straight tees and grooved flange adapters.




FIGURE 33: Tee-Pulling Tool



FIGURE 34: Mechanical Coupling

APPENDIX — ORGANIZATIONS

AFSA - American Fire Sprinkler Association
9696 Skillman, Suite 300
Lock Box 37
Dallas, TX 75243
(214) 349-5965 www.sprinklernet.org

AGA - American Gas Association
400 Capital Street
Washington, D.C. 20001
(202) 824-7000 www.aga.org

ANSI - American National Standards Institute
1819 L Street
Washington, D.C. 20036
(202) 293-8020 www.ansi.org

APFA - American Pipe Fittings Association
111 Park Place
Falls Church, VA 22046-4513
(703) 538-1786 www.apfa.com

ASHRAE - American Society of Heating, Refrigeration & Air-Conditioning Engineers, Inc.
1791 Tullie Circle, NE
Atlanta, GA 30329-2305
(404) 636-8400 www.ashrae.org

ASME - American Society of Mechanical Engineers
3 Park Avenue
New York, NY 10016
(212) 591-7000 www.asme.org

ASPE - American Society of Plumbing Engineers
3617 Thousand Oaks Blvd., Suite 210
Westlake Village, CA 91362
(805) 495-7120 www.aspe.org

ASNT - American Society for Non-destructive Testing
P.O. Box 28518
4153 Arlingate Plaza
Columbus, OH 43228-0518
(800) 222-2768 www.asnt.org

ASSE - American Society of Sanitary Engineers
901 Canterbury, Suite A
Westlake, OH 44145
(440) 835-3040
www.asse-plumbing.org

ASTM - American Society for Testing & Materials
100 Barr Harbor Drive
West Conshohocken, PA 19428-2959
(610) 832-9585 www.astm.org

AWS - American Welding Society
550 NW LeJeune Road
Miami, FL 33126-0440
(305) 443-9353 www.aws.org

AWWA - American Water Works Association
6666 W. Quincy Avenue
Denver, CO 80235
(303) 794-7711 www.awwa.org

CDA - Copper Development Association Inc.
260 Madison Avenue (16th floor)
New York, NY 10016
(212) 251-7200 www.copper.org

CGA - Compressed Gas Association, Inc.
4221 Walney Road, (5th floor)
Chantilly, VA 20151-2923
(703) 788-2700 www.cganet.com

CIPH - Canadian Institute of Plumbing and Heating
Suite 330, 295 The West Mall
Toronto, Ontario, M9C 4Z4
(416) 695-0447 www.ciph.com

CCBDA - Canada Copper and Brass Development Association
49 The Donway West (Suite 415)
North York, Ontario, M3C 3M9
(416) 391-5591
www.coppercanada.ca

GAMA - Gas Appliance Manufacturers Association
2107 Wilson Blvd., Suite 600
Arlington, VA 22201
(703) 525-7060 www.gamanet.org

IAPMO - International Association of Plumbing and Mechanical Officials
20001 Walnut Drive, South
Walnut, CA 91789
(909) 595-8449 www.iapmo.org

ICC - International Code Council
5203 Leesburg Pike (Suite 600)
Falls Church, VA 22041
(703) 931-4533 www.intlcode.org

MCAA - Mechanical Contractors Association of America
1385 Picard Drive
Rockville, MD 20832-4340
(301) 869-5800 www.mcaa.org

NACE - National Association of Corrosion Engineers
1440 South Creek Drive
Houston, TX 77084-4906
(281) 228-6200 www.nace.org

NFPA - National Fire Protection
Association
One Batterymarch Park
Quincy, MA 02269-9703
(800) 344-3555 www.nfpa.org

NFSA - National Fire Sprinkler
Association
P.O. Box 1000
40 John Barrett Road
Patterson, NJ 12563
(914) 878-4200 www.nfsa.org

NSF - National Sanitation Foundation
789 West Dixboro Road
Ann Arbor, MI 48113-0140
(734) 796-8010 www.nsf.org

PPFA - Plastic Pipe and Fitting
Association
800 Roosevelt Road, Bldg. C, Suite 20
Glen Ellyn, IL 60137
(630) 858-6540 www.ppfahome.org

SMACNA - Sheet Metal and Air
Conditioning Contractors National
Association
4201 Lafayette Center Drive
Chantilly, VA 20151-1209
(703) 803-2980 www.smacna.org

UA - United Association of Journeymen
and Apprentices of the Plumbing
and Pipefitting Industry of the
United States and Canada
901 Massachusettes Avenue, NW
Washington, D.C. 20001
(202) 268-5823 (Training Dept.)
www.ua.org



Application Handbooks

Water Supply and Distribution

Fuel Gas Distribution

Guide Specifications

Product Sources

How Tube is Made

Visit
www.copper.org

Soldering & Brazing

Air-Conditioning & Refrigeration

Builder Satisfaction Program

Fire Protection

Medical Gas

Properties

50-Year Warranty

